

78 75

ESCOBAR - ÚRIBE ASOCIADOS

ABOGADOS

Carrera 11A No. 94-76 Of. 305 - P.O. Box 94948, Bogotá, Colombia, S.A.
Tels.: (571) 6162151 - 6162061 - 6161839 - 6161889

Fax: (571) 6161889

2789/P

SUPERINTENDENCIA DE INDUSTRIA Y COMERCIO DIVISION DE NUEVAS CREACIONES

E. S. D.

SUPERINDUSTRIA Y COMERCIO

Radicación: 03609967 03609964

Folios: 42

Fecha (USD): 2005-05-06 16:23:16

Tramite: 232 PATENTES D 1 REGISTRO/ 444 REPUESTA

Dependencia: 2029 DIVISION DE NUEVAS CREACIONES

Ref.: Expediente No. 05.009.967
Solicitud de Patente a nombre de
McNeil-PPC, Inc.

Yo, JIMENA ESCOBAR URIBE, identificada como aparece al pie de mi firma, domiciliada en la Carrera 11 A No. 94-76, of. 305, obrando como apoderada de la sociedad McNeil-PPC, Inc., en respuesta al Oficio No. 12206 notificado por fijación en lista el día 24 de febrero de 2005 domiciliada en Skillman, New Jersey, Estados Unidos de América, solicitante de la patente de la referencia, me permito presentar los siguientes documentos:

1. Dibujos formales (los cuales fueron anunciados en el capítulo descriptivo) de acuerdo con lo establecido en el artículo 4-d del Decreto 117 de 1994.
2. Artes finales en tamaño 12 x 12 centímetros (por duplicado) de la figura característica.
3. Copia certificada de la solicitud de Patente número 10/039,239 presentada en Estados Unidos de América el día 19 de enero de 2005, la cual equivale a la solicitud provisional No. 60/542,521 presentada junto con mi memorial de 7 de marzo de 2005. con la debida traducción de lo pertinente, incluyendo el capítulo reivindicatorio.

Espero con esto haber dado cabal cumplimiento a lo solicitado por ese despacho y de conformidad con lo indicado en los artículos 3º, inciso 3; 35, inciso 2 y 59, inciso 2 del CCA, al analizar este memorial, atentamente ruego se traten todas las cuestiones planteadas con motivo del mismo.

Señor Superintendente,


JIMENA ESCOBAR URIBE
C.C.39.779.452 de Usaquén
T.P. 68228
Cód. 5376




FIG. 1




FIG. 2

87
28

ESTADOS UNIDOS DE AMERICA
A TODOS AQUELLOS A QUIENES EL PRESENTE LLEGUE:

DEPARTAMENTO DE COMERCIO DE LOS ESTADOS
UNIDOS
Oficina de Patentes y Marcas de los Estados Unidos

Marzo 24, 2005

La presente es para certificar que el anexo es una copia fiel de los registros de la Oficina de Patentes y Marcas de los Estados Unidos, de los documentos de la solicitud de patente identificada más adelante, que cumplieron con los requerimientos para concederse una fecha de presentación de acuerdo con 35 USC 111.

Número de Solicitud: 10/039,239

Fecha de Presentación: Enero 19 de 2005

Por la autoridad del
Comisionado de Patentes y Marca

(fdo) H.L. JACKSON
Oficial Certificador
Sello oficial de la Oficina de Patentes y Marcas de los
Estados Unidos de América

NOVEDAD DE LA INVENCION

REIVINDICACIONES

- 5 1.- Un método para aplicar una mezcla de adhesivo/superabsorbente a un sustrato, que comprende los pasos de: calentar una mezcla de adhesivo y polímero superabsorbente a una primera temperatura, a una primera presión, la primera temperatura es menor a la temperatura de ebullición de la mezcla a la primera presión, pasar la mezcla
- 10 calentada a través de un intercambiador de calor a una segunda presión, la segunda presión es mayor a la primera presión, el intercambiador de calor está adaptado para elevar la temperatura de la mezcla a una segunda temperatura que es mayor a dicha primera temperatura; y aplicar de manera selectiva la mezcla a un sustrato.
- 15 2.- El método de conformidad con la reivindicación 1, caracterizado además porque dicha primera presión es sustancialmente igual a presión ambiental.
- 3.- El método de conformidad con la reivindicación 1, caracterizado además porque dicha mezcla se aplica a dicho sustrato
- 20 mediante un aplicador de adhesivo.
- 4.- El método de conformidad con la reivindicación 3, caracterizado además porque dicho aplicador de adhesivo es un revestidor por ranuras

5.- El método de conformidad con la reivindicación 1, caracterizado además porque dicho substrato se mueve a una velocidad en la escala de 152.4 - 304.8 m/min.

6.- El método de conformidad con la reivindicación 3, caracterizado además porque dicha mezcla se calienta en un tanque de calentamiento.

7.- El método de conformidad con la reivindicación 6, caracterizado además porque comprende adicionalmente: transportar dicha mezcla a través de una primera longitud de conducto dispuesto entre dicho tanque de calentamiento y dicho intercambiador de calor; y transportar dicha mezcla a través de una segunda longitud de conducto dispuesto entre dicho intercambiador de calor y dicho aplicador de adhesivo.

8.- El método de conformidad con la reivindicación 7, caracterizado además porque comprende adicionalmente: calentar dicha primera longitud de conducto para mantener una temperatura de dicha mezcla dentro de dicha primera longitud de conducto sustancialmente constante.

9.- El método de conformidad con la reivindicación 7, caracterizado además porque comprende adicionalmente: calentar dicha segunda longitud de conducto para mantener una temperatura de dicha mezcla dentro de dicha segunda longitud de conducto sustancialmente constante.

10.- El método de conformidad con la reivindicación 1, caracterizado además porque dicha primera temperatura está en la escala de aproximadamente 93.3°C a aproximadamente 121°C.

11.- El método de conformidad con la reivindicación 1,
5 caracterizado además porque dicha segunda temperatura está en la escala de aproximadamente 121°C a aproximadamente 177°C.

12.- El método de conformidad con la reivindicación 1, caracterizado además porque dicha primera temperatura es de aproximadamente 121°C y dicha segunda temperatura es de
10 aproximadamente 149°C.

13.- El método de conformidad con la reivindicación 1, caracterizado además porque dicho adhesivo se aplica a una velocidad de aproximadamente 45 gsm a aproximadamente 80 gsm.

14.- El método de conformidad con la reivindicación 1,
15 caracterizado además porque dicho sustrato es un sustrato no tejido.

15 - El método de conformidad con la reivindicación 1, caracterizado además porque dicha segunda presión está en la escala de aproximadamente 3.51 kg/cm² a aproximadamente 35.15 kg/cm².

16.- Un sistema para aplicar una mezcla de
20 adhesivo/superabsorbente a un sustrato, que comprende: un tanque de calentamiento para calentar una mezcla de adhesivo y polímero superabsorbente a una primera temperatura, a una primera presión, la primera temperatura es menor que la temperatura de ebullición de la mezcla en la

primera presión; un intercambiador de calor en comunicación de flujo con el tanque de calentamiento para calentar la mezcla a una segunda presión, la segunda presión es mayor a la primera presión, el intercambiador de calor está adaptado para elevar la temperatura de la mezcla a una segunda
5 temperatura que es mayor a dicha primera temperatura; y un aplicador de adhesivo en comunicación de flujo con el intercambiador de calor para aplicar de manera selectiva la mezcla a un sustrato.

17.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicha primera presión es sustancialmente igual
10 a presión ambiental.

18.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicho aplicador de adhesivo es un revestidor por ranuras.

19.- El sistema de conformidad con la reivindicación 16,
15 caracterizado además porque dicho sustrato es un sustrato móvil que se mueve a una velocidad en la escala de 152.4 - 304.8 m/min.

20.- El sistema de conformidad con la reivindicación 16, caracterizado además porque comprende adicionalmente: una primera longitud de conducto dispuesto entre y que conecta dicho tanque de
20 calentamiento y dicho intercambiador de calor; y una segunda longitud de conducto dispuesto entre y que conecta dicho intercambiador de calor y dicho aplicador de adhesivo.

21.- El sistema de conformidad con la reivindicación 20, caracterizado además porque comprende adicionalmente al menos un calentador estructurado y dispuesto para calentar dicha primera longitud de conducto y mantener una temperatura de dicha mezcla dentro de dicha primera longitud de conducto sustancialmente constante.

22.- El sistema de conformidad con la reivindicación 20, caracterizado además porque comprende adicionalmente al menos un calentador estructurado y dispuesto para calentar dicha segunda longitud de conducto y mantener una temperatura de dicha mezcla dentro de dicha segunda longitud de conducto sustancialmente constante.

23 - El sistema de conformidad con la reivindicación 16, caracterizado además porque dicha primera temperatura está en la escala de aproximadamente 93.3°C a aproximadamente 121°C.

24.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicha segunda temperatura está en la escala de aproximadamente 121°C a aproximadamente 177°C.


25.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicha primera temperatura es de aproximadamente 121°C y dicha segunda temperatura es de aproximadamente 149°C.

26.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicho aplicador de adhesivo está estructurado y

dispuesto para aplicar dicho adhesivo a dicho sustrato a una velocidad de aproximadamente 45 gsm a aproximadamente 80 gsm.

27.- El sistema de conformidad con la reivindicación 16, caracterizado además porque dicha segunda presión está en la escala de 5 aproximadamente 3.51 kg/cm² a aproximadamente 35.15 kg/cm².

PA 1298768



THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME;

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

March 24, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 11/039,239




FILING DATE: *January 19, 2005*

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



H. L. Jackson
H. L. JACKSON
Certifying Officer

21
86

UTILITY PATENT APPLICATION TRANSMITTAL		Attorney Docket No.	PPC-5043-USNP									
		First Inventor	Paul Y. Fung									
		Title	METHOD AND SYSTEM FOR APPLYING ABSORBENT MATERIAL TO A SUBSTRATE									
Utility for new nonprovisional applications under 37 CFR 1.53(b)		Express Mail Label No.	EL 960327398 US									
APPLICATION ELEMENTS See MPEP Chapter 600 concerning utility patent application contents		ADDRESS TO: Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450										
1. ☒ Fee Transmittal Form (e.g., PTO/SB/17) (submit an original and a duplicate for fee processing) 2. ☐ Applicant claims small entity status. 3. ☒ Specification [Total Pages 20] (Preferred arrangement set forth below) - Descriptive Title of the Invention - Cross Reference to Related Applications - Statement Regarding Fed sponsored R&D - Reference to sequence listing, a table, or a computer program listing appendix - Background of the Invention - Brief Summary of the Invention - Brief Description of the Drawings (if filed) - Detailed Description - Claim(s) - Abstract of the Disclosure 4. ☒ Drawing(s) (35 USC 113) [Total Sheets 2] 5. Oath or Declaration [Total Pages 4] a. ☒ Newly unexecuted (original or copy) b. ☐ Copy from a prior application (37 CFR 1.63(d)) (for continuation/divisional with Box 18 completed) i. ☐ DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37 CFR 1.63(d)(2) and 1.33(b). 6. ☐ Application Data Sheet. See 37 CFR 1.76		7. ☐ CD-ROM or CD-R in duplicate, large table or Computer Program (Appendix) 8. Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary) a. ☐ Computer Readable Form (CRF) b. ☐ Specification Sequence Listing on: i. ☐ CD-ROM or CD-R (2 copies); or ii. ☐ paper c. ☐ Statement verifying identity of above copies ACCOMPANYING APPLICATION PARTS 9. ☐ Assignment Papers (cover sheet & document(s)) 10. ☐ 37 CFR 3.73(b) Statement ☐ Power of Attorney (when there is an assignee) 11. ☐ English Translation Document (if applicable) 12. ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations 13. ☐ Preliminary Amendment 14. ☒ Return Receipt Postcard (MPEP 503) (Should be specifically itemized) 15. ☐ Certified Copy of Priority Document(s) (if foreign priority is claimed) 16. ☐ Request and Certifications under 35 U.S.C. 122 (b)(2)(B)(i). Applicant must attach form PTO/SB/35 or its equivalent. 17. ☐ Other										
18. ☐ If a CONTINUING APPLICATION, check appropriate box and supply the requisite information below and in a preliminary amendment, or in an Application Data Sheet under 37 CFR 1.76. ☐ Continuation ☐ Divisional ☐ Continuation-in-Part (CIP) of prior application No.: , filed . Prior application information: Examiner Group Art Unit: For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 5b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation <u>can only</u> be relied upon when a portion has been inadvertently omitted from the submitted application parts.												
19. CORRESPONDENCE ADDRESS ☒ Customer Number or Bar Code Label 000027777 or ☐ Correspondence Address below Name: Philip S. Johnson, Esq. Address: Johnson & Johnson One Johnson & Johnson Plaza New Brunswick, NJ 08933-7003 USA												
20. TELEPHONE CONTACT Please direct all telephone calls or telefaxes to Paul J. Higgins at: Telephone: (732) 524-1728 Fax: (732) 524-2808												
21. SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT REQUIRED <table border="1"><tr><td>NAME</td><td>Paul J. Higgins</td><td>Reg. No. 44,152</td></tr><tr><td>SIGNATURE</td><td colspan="2"></td></tr><tr><td>DATE</td><td colspan="2">January 19, 2005</td></tr></table>				NAME	Paul J. Higgins	Reg. No. 44,152	SIGNATURE			DATE	January 19, 2005	
NAME	Paul J. Higgins	Reg. No. 44,152										
SIGNATURE												
DATE	January 19, 2005											

22
87

FEE TRANSMITTAL	<i>Complete if Known</i>	
	Application Number	Unassigned
	Filing Date	January 19, 2005
	First Named Inventor	Paul Y. Fung
	Group Art Unit	Unassigned
	Examiner Name	Unassigned
	Attorney Docket Number	PPC-5043-USNP

FEE CALCULATION

CLAIMS AS FILED

(1)	(2)	(3)	(4)	(5)
FOR:	NUMBER FILED	NUMBER EXTRA	RATE	BASIC FEE \$300.00
TOTAL CLAIMS	27 - 20 =	7	x 50.00	\$ 350.00
INDEPENDENT CLAIMS	2 - 3 =	0	x 200.00	\$ 0.00
MULTIPLE DEPENDENT CLAIMS	☐	N/A	\$200.00	
			TOTAL FEES	\$ 650.00

METHOD OF PAYMENT

- ☒ Please charge Deposit Account No. 10-0750/PPC-5043-USNP/PJH in the amount of \$650.00. Three copies of this sheet are enclosed.
- ☒ The Commissioner is hereby authorized to charge any additional fees which may be required in connection with the filing of this communication, or credit any overpayment, to Account No. 10-0750/PPC-5043-USNP/PJH. Three copies of this sheet are enclosed.

SUBMITTED BY:			<i>Complete (if applicable)</i>
Typed or Printed Name	Paul J. Higgins		Reg. No. 44,152
Signature		Date: January 19, 2005	Deposit Account No. 10-0750

25
88

DOCKET NO. PPC-5043-USNP

IN THE UNITED STATES
PATENT AND TRADEMARK OFFICE

Applicant: Fung et al.

For : METHOD AND SYSTEM FOR APPLYING ABSORBENT MATERIAL
TO A SUBSTRATE

Express Mail Certificate

"Express Mail" mailing number: EL 960327398 US

Date of Deposit: January 19, 2005

I hereby certify that this complete application, including specification pages, claims, and drawings, is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

A Combined Declaration and Power of Attorney will be submitted to the United States Patent and Trademark Office upon receipt of the U.S. Serial Number for this patent application.

Laurie A. Phillips
(Typed or printed name of person mailing paper or fee)

(Signature of person mailing paper or fee)

94
89

**METHOD AND SYSTEM FOR APPLYING ABSORBENT MATERIAL
TO A SUBSTRATE**

5 Cross-Reference to Related Applications

This application claims priority to Application No. 60/542,521 filed on February 5, 2004.

Field of the Invention

10 The present invention relates to a method and system for selectively applying an absorbent material to the surface of a substrate, and in particular, a method and system for applying a super absorbent polymer (SAP) and adhesive mixture to a substrate.

15 Background of the Invention

Absorbent articles such as, for example, disposable diapers, sanitary napkins, pantliners, etc., are well known in the art. Known absorbent articles may typically include, for example, a fluid permeable coverstock, a fluid impermeable back sheet and an absorbent core supported therebetween. Traditionally, absorbent cores include
20 loosely formed cellulosic fibers and may also contain superabsorbent polymer fibers to improve the absorbent capacity of the core. The term "superabsorbent polymer" (or "SAP") as used herein, generally refers to materials which are capable of absorbing and retaining at least about 10 times their weight in body fluids under a 0.5 psi pressure. Such superabsorbent polymers include crosslinked hydrophilic polymers,
25 such as polyvinyl alcohols, polyethylene oxides, crosslinked starches, guar gum, xanthan gum, and the like. One commercially available SAP material is AQUAKEEP SA-70, available from Sumitomo Seika Chemicals Co., Ltd.

Due to the loosely formed nature of traditional cores, such cores are rather thick and bulky in nature. More recently, in an effort to reduce the overall thickness and bulkiness of absorbent articles, particularly in feminine pads, sanitary napkins, pantliners and the like, the traditional loosely formed absorbent core, has been replaced with a thin highly absorbent web material which frequently includes, in part, a SAP particulate material. As discussed in further detail below, the highly absorbent web material is typically formed by either incorporating the SAP particulate in the web during the web forming process, or in the alternative, the SAP particulate may be mechanically applied (using nozzles or the like) to the web after the web forming process.

A SAP particulate material may be incorporated into a web directly during the web forming process using any one of a number of known non-woven web forming techniques (e.g. air laid). During these processes, the SAP particulate material is incorporated into the web material by mixing SAP particulate material with the other fibrous components of the web prior to the formation of the web. The other fibrous components of the web may include cellulosic fibers such as wood pulp fibers, cotton linters, rayon fibers, flax, jute and the like. Hydrophilic synthetic fibers, such as polyethylene, polypropylene, nylon, polyester and the like, may be used in lieu of or in combination with cellulosic fibers.

As discussed above, the SAP particulate material may alternatively be applied to a web substrate after the web has been formed. Typically the SAP particulate is applied to the web by using mechanical delivery devices such as conduits, nozzle sprayers, and the like to thereby apply the SAP particulate material to the web. A method and system for the application of SAP particulate material to a web in this manner is described in U.S. Patent No. 5,248,524. Optionally, an adhesive may be

26
21

applied to the substrate prior to the application of the SAP material so that the superabsorbent adheres to the substrate in those areas where the adhesive has been applied. Slot coaters, such as the commercially available Nordson EP-11 and the Nordson EP-45, from Nordson, and spray style applicators may be used to apply the adhesive to the web substrate.

Unfortunately, both of the prior art techniques described above have inherent drawbacks. For example, mixing the SAP material and the fibrous components of the web prior to the formation of the web normally results in the SAP material being uniformly dispersed through the web. In some applications, this may not be desired.

For example, in some applications, it may be preferable to selectively apply the SAP material only to a portion of the substrate or it may be desirable to apply the SAP material to the substrate in a selected pattern. Further, depending on the particular fibrous material(s) that forms the web, it may not be desirable to mix the SAP material with the fibrous material prior to the formation of the web, since the materials may not be mutually compatible. Likewise, using conduits, nozzles, and the like to deliver the SAP material to a formed web substrate, particularly a substrate moving at a high speed, is also subject to variety of problems. For example, it is difficult to apply the SAP material to a pre-determined, localized area of the substrate.

In particular, if the spraying of the SAP material is not initiated and terminated within a tightly defined time interval, the SAP particulate may be delivered to undesired locations rather than the desired location on the substrate. Furthermore, the SAP particulate material is often subject to spreading, *i.e.*, the particulate does not remain localized on the substrate and the particulate may migrate to locations where it is not desired, thereby contaminating the process. The above problems are compounded for

27
92

non-woven substrates which are often processed at line speeds that are fast enough to promote scattering of the SAP particulate to undesired locations on the substrate.

In view of the above, a need exists for a method of applying a superabsorbent material to a substrate that overcomes one or more of the above-mentioned

5 drawbacks.

98
43

Summary of the Invention

According to a first aspect of the invention, the present invention provides a method for applying an adhesive/superabsorbent mixture to a substrate including the steps of:

5 heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, the first temperature being less than the boiling temperature of the mixture at the first pressure;

 passing the heated mixture through a heat exchanger at a second pressure, the second pressure being higher than the first pressure, the heat exchanger being adapted
10 to raise the temperature of the mixture to a second temperature that is higher than said first temperature; and

 selectively applying the mixture to a substrate.

According to a second aspect of the invention, the present invention provides a system for applying an adhesive/superabsorbent mixture to a substrate including:

15 a heating tank for heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, the first temperature being less than the boiling temperature of the mixture at the first pressure;

 a heat exchanger in flow communication with the heating tank for heating the mixture at a second pressure, the second pressure being higher than the first pressure,
20 the heat exchanger being adapted to raise the temperature of the mixture to a second temperature that is higher than the first temperature; and

 an adhesive applicator in flow communication with the heat exchanger for selectively applying the mixture to a substrate.

90
94

Brief Description of the Drawings

A more detailed description of the invention is provided below, with reference to the appended drawings in which:

Fig. 1 is a schematic view of a prior art system for applying an adhesive and
5 superabsorbent particulate material to a substrate; and

Fig. 2 is a schematic view of the system according to the present invention for applying superabsorbent/adhesive mixture to a substrate.

196
a5

Detailed Description of the Invention

As discussed briefly in the "Background of the Invention" section above, one of the known techniques for adhering superabsorbent polymer, in particulate or fibrous form, to a substrate includes the steps of coating a surface of the substrate with an adhesive and applying superabsorbent material to the coated substrate using mechanical delivery devices such as conduits, nozzle sprayers. In this manner the SAP adheres to the web. A process of this type generally includes the following steps:

- 10 (1) heating an adhesive in a heating tank;
- (2) pumping the adhesive through a conduit to an adhesive applicator for applying the adhesive to the substrate;
- (3) applying the superabsorbent particulate material to the coated substrate using conduits, nozzle sprayers, or the like.

15 The manufacturers of the adhesives used in the above described process typically specify the recommended temperature to which the adhesive should be heated prior to pumping the same to the applicator. The specific temperature to which the adhesive should be heated varies with the specific composition of the adhesive, however the specified temperature is below the boiling point of the adhesive at ambient pressure and yet high enough to sufficiently reduce the viscosity of the adhesive to permit the adhesive to be easily pumped from the tank to the adhesive applicator.

20 As shown in Figure 1, a conventional prior art system 100 for carrying out the above described process generally includes a heating tank 102, an adhesive applicator 104 for applying the adhesive to a moving web substrate 111 and a nozzle 108 or the

101
96

like for applying superabsorbent particulate 109 to the web. A conduit 106 interconnects the tank 102 and the adhesive applicator 104 to convey adhesive from the heating tank 102 to the adhesive applicator 104 for application of the adhesive to the web 111. Conventional heating tanks typically include an integrated pump to convey the heated adhesive through the conduit 106. After the adhesive applicator 104 applies the adhesive to the web 111, the web is conveyed in a machine direction to the nozzle 108 or the like for applying the superabsorbent particulate 109 to the web. Conventionally, the conduit 106 is insulated and a plurality of heaters are often arranged in proximity to the conduit 106 to maintain the temperature of the adhesive substantially constant between the tank 102 and the adhesive applicator 104.

Commercially available heating tanks of the type used in the above system include the Nordson 3600, Orson 6000, Meltex GR and Meltex MX tanks from the Nordson Corporation. These tanks, like other such conventional tanks, have a pump incorporated therein to enable the heated adhesive to be pumped through the attached conduit to the adhesive applicator. A conventional adhesive applicator of the type used in the above described method above may comprise, for example, a slot coater. Suitable commercially available slot coaters include the Nordson EP-11 and EP-45 manufactured by the Nordson Corporation.

As discussed in the "Background" section above, prior art systems of the type shown in Figure 1 have inherent drawbacks. For example, since the superabsorbent particulate material is essentially sprayed on the coated web it is difficult to apply the particulate material to a pre-determined, localized area of the substrate. In particular, if the spraying of the powder is not initiated and terminated within a tightly defined time interval, the particulate may be delivered to undesired locations on the substrate. Furthermore, the particulate material is often subject to spreading, *i.e.*, the particulate

102.
JAX

does not remain localized on the substrate and the particulate may migrate to locations where it is not desired, thereby contaminating the process..

In an effort to overcome the problems associated with the prior art process described with reference to Figure 1, adhesive/superabsorbent polymer particulate mixtures have been developed that are intended be applied in a single step using a conventional heating tank and adhesive applicator. In this manner, the separate step of applying the superabsorbent polymer to the coated web, by a nozzle or the like, is eliminated. A commercially available superabsorbent/adhesive mixture is Fuller NW-1078, from the Fuller Corp. However, as discussed in greater detail below, the inventors of the present invention have discovered that there are inherent difficulties associated with the application of superabsorbent/adhesive mixtures when using conventional heating tank-applicator systems of the type shown in Figure 1 and described above with reference thereto.

Mixing superabsorbent particulate material with adhesive increases the viscosity of the resultant mixture as compared to the viscosity of the adhesive alone. Consequently, when the mixture is heated in a conventional heating tank to a temperature below the boiling point of the mixture, at ambient pressure, the viscosity of the mixture cannot be reduced to a sufficient extent to thereby permit a pump in a conventional heating tank to adequately convey the mixture to the coater at an acceptable flow rate. Rather, due to the increased viscosity of the mixture, as compared to the adhesive alone, the pump is only able to convey the mixture at a reduced flow rate. Further, it has been discovered that in order to reduce the viscosity of the mixture to an acceptable level, i.e. to a level where a pump of the type included with conventional heating tanks can convey the mixture at an acceptable flow rate, the mixture must be heated to a temperature in excess of the boiling point of the mixture

103
98

at ambient pressure. Heating the mixture to such a high temperature is not acceptable, however, since boiling the mixture results in pump cavitations which also results in a reduction in the flow rate. Yet another problem with using conventional heating tank-coater systems to apply a superabsorbent/adhesive mixture is the pressure caused
5 within the system is often higher than the equipment rating. Again, this is caused by the high viscosity of the superabsorbent/adhesive mixture. Still another problem with using conventional heating tank-coater systems to apply a superabsorbent/adhesive mixture to a substrate is that the applicator can accumulate a build up of the of the mixture, resulting from the high viscous nature of the mixture, thereby causing
10 clogging.

In view of the above, the method according to the present invention includes the steps of:

- (1) heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, the first temperature being less than the boiling
15 temperature of the mixture at the first pressure;
- (2) pumping the heated mixture through a heat exchanger at a second pressure, the second pressure being higher than the first pressure, the heat exchanger being adapted to raise the temperature of the mixture to a second temperature that is higher than the first temperature;
- (3) selectively applying the mixture to a substrate.

Figure 2 schematically depicts a system 200 for carrying out the method according to the present invention. The system 200 comprises a heating tank 202, a heat exchanger 203 and an adhesive applicator 204 for applying an
adhesive/superabsorbent polymer mixture to a substrate 211. The system further
25 includes a first length of conduit 205 that connects the heating tank 202 to the heat

100-
99

exchanger 203 and a second length of conduit 207 that connects the heat exchanger 203 with the adhesive applicator 204. The heating tank 202 includes an integrated pump for conveying the adhesive through the first length of conduit 205, through the heat exchanger 203, through the second length of conduit 207, to the adhesive applicator 204.

The Nordson 3600 tank from the Nordson Corporation may be used as the heating tank 202 and the Nordson EP-11, also manufactured by the Nordson Corporation, may be used as the adhesive applicator 204.

Clearly, the diameter of the conduits 205 and 207 have a reduced diameter relative to the diameter of the heating tank 202. Thus, the superabsorbent/adhesive mixture is conveyed through the conduits 205 and 207 at a pressure that is higher than a pressure present in the heating tank 202. The heat exchanger 203 is preferably constructed from a coiled pipe (not shown in the figures) having a diameter that is the same as the conduits 205 and 207 and also includes a plurality of heaters (not shown) that are structured and arranged to raise the temperature of the mixture within the heat exchanger. Since the superabsorbent/adhesive mixture is conveyed through the heat exchanger 203 under pressure (i.e. at a higher pressure relative to the pressure present in the tank 202) the heat exchanger 203 can heat the superabsorbent/adhesive mixture to a temperature that would exceed the boiling point temperature of the mixture at the pressure present in the heating tank 202. However, since the pressure is higher in the heat exchanger, relative to the pressure in the heating tank 202, the temperature of the superabsorbent/adhesive mixture may be raised without boiling the mixture.

Moreover, by raising the temperature of the superabsorbent/adhesive mixture in the heat exchanger the viscosity of the mixture is reduced. The reduction in the viscosity of the superabsorbent/adhesive mixture functions to reduce the overall

105
100

pressure experienced by the system thereby permitting a standard pump in a commercially available heating tank to convey the superabsorbent/adhesive through the system at rate that is acceptable for manufacturing purposes. More specifically, the system shown in Fig. 2 permits a the superabsorbent/adhesive mixture to be
5 intermittently or continuously applied, using a conventional applicator, to a substrate moving at speeds in the range of 500-1000 fpm with an add-on level of the adhesive in the range of 45-80 gsm.

Example #1

10 A heating tank-coater system was constructed in accordance with the system depicted in figure 1. A Nordson 3600 heating tank was used as the heating tank. The pump included in the heating tank was a 0.833 cc/rev pump . The adhesive applicator was a Nordson EP-45 coater having a .010" thick shim with a 12.5 opening. A conventional 5/16" I.D. insulated hose was used to convey the adhesive/superabsorbent
15 mixture from the heating tank to the applicator. A plurality of conventional heaters were arranged around the hose to maintain the fluid temperature substantially constant within the hose.

Fuller NW-1078 was used as the adhesive/superabsorbent mixture. The substrate speed was set at 850 fpm and the add-on level for applying the
20 adhesive/superabsorbent mixture to the substrate was set to apply the adhesive mixture at a target rate of 65 gsm.

Using the above described system it was observed that heating the adhesive/superabsorbent mixture in the tank to a temperature higher than 250° F caused the mixture to boil, which in turn caused cavitation at the pump. The pump
25 cavitation in turn caused inconsistent adhesive add-on levels. It was further observed

108
101

that heating the adhesive/superabsorbent mixture to a temperature below 250° resulted in the adhesive/superabsorbent mixture being too viscous, resulting in excessive pressure within the system, thereby causing pump failure.

5 **Example #2**

A system according to the present invention was constructed in the manner depicted in Figure 2. A Nordson 3600 heating tank was used as the heating tank the applicator was a Nordson EP-45 coater having with a .010" thick shim with a 12.5 opening. The pump included in the heating tank was a 0.833 cc/rev pump .

10 A heat exchanger was arranged between the heating tank and the applicator.

The heat exchanger consisted of an coiled aluminum tube and a plurality of cartridge heaters arranged in heat transfer relationship with the coiled tube. The inner diameter of the aluminum tube was approximately 5/16" I.D. and the tube had an overall length of about 12 feet. A first length of 5/16" I.D. insulated hose was used to connect the heating tank to a first end of the aluminum tubing. A second length of 5/16" I.D. hose was used to connect a second end of the aluminum tubing with the applicator.

15 Fuller NW-1078 was used as the adhesive/superabsorbent mixture. The substrate speed was set at 850 fpm and the add-on level for applying the adhesive/superabsorbent mixture was set to apply the adhesive mixture at a target rate of 65 gsm.

20 The adhesive/superabsorbent mixture was heated to a temperature of 250° F in the heating tank and conveyed through the first length of tubing to the heat exchanger. Conventional heaters were arranged about the first length of tubing to maintain the temperature within the first length of tubing substantially constant at 250°.

107
102

Cartridge heaters were arranged about aluminum tubing of the heat exchanger, and the heaters were set to raise the temperature of the adhesive/superabsorbent mixture within the heat exchanger from a temperature of 250° F to a temperature of 300° F. The flow rate of the adhesive/superabsorbent mixture through the heat exchanger was measured to be about 65 grams per minute. Heaters were arranged around the second length of hose between the heat exchanger and the applicator to substantially maintain the temperature of the mixture within the second length of hose at approximately 300°.

The heat exchanger functioned to raise the temperature of the adhesive/superabsorbent mixture and thereby lower the viscosity of the adhesive/superabsorbent mixture resulting in reduction of the overall pressure in the system. This allowed the a 0.833 cc/rev pump in the Nordson 3600 heating tank to effectively convey the adhesive through the system so that the target add-on of 65 gsm of the adhesive/superabsorbent mixture was met at the substrate speed of 850 fpm.

The method and system according to the present invention has been described above with reference to the application of an adhesive/superabsorbent mixture to a continuous substrate. However, the same method and system could also be used to apply such a mixture to discrete articles, such as disposable diapers, sanitary napkins, pantliners, etc.

The foregoing disclosure is directed to various specific embodiments of the present invention, however, other further embodiments maybe devised without departing from the scope of the present invention.

198
103

Claims

We claim:

1. A method for applying an adhesive/superabsorbent mixture to a substrate

5 comprising the steps of:

heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, said first temperature being less than the boiling temperature of said mixture at said first pressure;

10 passing the heated mixture through a heat exchanger at a second pressure, the second pressure being higher than the first pressure, the heat exchanger being adapted to raise the temperature of the mixture to a second temperature that is higher than said first temperature; and

selectively applying the mixture to a substrate.

15 2. The method according to claim 1, wherein said first pressure is substantially equal to ambient pressure.

3. The method according to claim 1, wherein said mixture is applied to said substrate by an adhesive applicator.

20

4. The method according to claim 3, wherein said adhesive applicator is a slot coater.

5. The method according to claim 1, wherein said substrate is moving at a speed in the range of 500-1000 fpm.

25

128
104

6. The method according to claim 3, wherein said mixture is heated in a heating tank.

7. The method according to claim 6, further comprising:

conveying said mixture through a first length of conduit arranged between said

5 heating tank and said heat exchanger; and

conveying said mixture through a second length of conduit arranged between said
heat exchange and said adhesive applicator.

8. The method according to claim 7, further comprising:

10 heating said first length of conduit to maintain a temperature of said mixture
within said first length of conduit substantially constant.

9. The method according to claim 7, further comprising:

heating said second length of conduit to maintain a temperature of said mixture

15 with said second length of conduit substantially constant.

10. The method according to claim 1, wherein said first temperature is in the range of
about 200° F to about 250° F.

20 11. The method according to claim 1, wherein said second temperature is in the range
of about 250° to about 350°.

12. The method according to claim 1, wherein said first temperature is about 250° F
and said second temperature is about 300° F.

25

105

13. The method according to claim 1, wherein said adhesive is applied at a rate of about 45 gsm to about 80 gsm.

14. The method according to claim 1, wherein said substrate is a non-woven substrate.

15. The method according to claim 1, wherein said second pressure is in the range of about 50 psi to about 500 psi.

16. A system for applying an adhesive/superabsorbent mixture to a substrate comprising:

a heating tank for heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, said first temperature being less than the boiling temperature of said mixture at said first pressure;

a heat exchanger in flow communication with said heating tank for heating said mixture at a second pressure, the second pressure being higher than the first pressure, the heat exchanger being adapted to raise the temperature of the mixture to a second temperature that is higher than said first temperature; and

an adhesive applicator in flow communication with said heat exchanger for selectively applying the mixture to a substrate.

17. The system according to claim 16, wherein said first pressure is substantially equal to ambient pressure.

111
106

18. The system according to claim 16, wherein said adhesive applicator is a slot
coater.

19. The system according to claim 16, wherein said substrate is a moving substrate
5 moving at a speed in the range of 500-1000 fpm.

20. The system according to claim 16, further comprising:

a first length of conduit arranged between and connecting said heating tank and
said heat exchanger; and

10 a second length of conduit arranged between and connecting said heat exchange
and said adhesive applicator.

21. The system according to claim 20, further comprising at least one heater
structured and arranged to heat said first length of conduit and maintain a temperature
15 of said mixture within said first length of conduit substantially constant.

22. The system according to claim 20, further comprising at least one heater structured
and arranged to heat said second length of conduit and maintain a temperature of said
mixture within said second length of conduit substantially constant.

20

23. The system according to claim 16, wherein said first temperature is in the range
of about 200° F to about 250° F.

24. The system according to claim 16, wherein said second temperature is in the
25 range of about 250° to about 350°.

Please type a plus sign (+) inside the box ☐

PTO/SB/01 (10-00)
Approved for use through 10/31/2002. OMB 0951-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

DECLARATION AND POWER OF ATTORNEY FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63) ☒ Declaration Submitted with Initial Filing OR ☐ Declaration Submitted after Initial Filing (Surcharge (37 CFR 1.16(e)) required)	Attorney Docket Number	PPC-5043-USNP	
	First Named Inventor	Paul Y. Fung	
	COMPLETE IF KNOWN		
	Application Number	Unassigned	
	Filing Date	January 19, 2005	
	Group Art Unit	Unassigned	
	Examiner Name	Unassigned	

As a below named inventor, I hereby declare that:

My residence, mailing address, and citizenship are as stated below next to my name.
I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled.

METHOD AND SYSTEM FOR APPLYING ABSORBENT MATERIAL TO A SUBSTRATE
(Title of the Invention)

the specification of which

☒ is attached hereto

OR

☐ was filed on (MM/DD/YYYY) as United States Application Number or PCT International Application Number and was amended on (MM/DD/YYYY)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
			☐ ☐ ☐ ☐	☐ ☐ ☐ ☐	☐ ☐ ☐ ☐

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

43-
108

DECLARATION - Utility or Design Patent Application		
I hereby claim the benefit under 35 U.S.C. 119(e) of any United States provisional application(s) listed below.		
Application Number(s)	Filing Date (MM/DD/YYYY)	☐ Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/028 attached hereto
60/542,521	February 5, 2004	
I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:		
Application Serial No.	Filing Date	Status
		Patented Patented Patented
I hereby appoint:		
☒ Practitioners at Customer Number 000027777 --		Place Customer Number Bar Code Label Here
AND		
☐ Practitioner(s) named below: <u>Name</u> <u>Registration Number</u>		
as my/our attorney(s) or agent(s) to prosecute the application identified above, and to transact all business in the United States Patent and Trademark Office connected therewith.		
Address all telephone calls to Paul J Higgins at telephone number (732) 524-1728		
Direct all correspondence to: ☒ Customer Number 000027777 OR ☐ Correspondence address below		
Name:		
Address:		
Address:		
City:	State:	ZIP
Country	Telephone:	Fax:

109

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.			
NAME OF SOLE OR FIRST INVENTOR:		☐ A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any)) PAUL Y.		Family Name or Surname FUNG	
Inventor's Signature		Date	
Residence: City South River	State NJ	Country USA	Citizenship U.S.A.
Mailing Address 22 Leland Avenue			
City South River	State NJ	ZIP 08865	Country U.S.A.
I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.			
NAME OF SECOND INVENTOR:		☐ A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any)) ANTHONY D.		Family Name or Surname ONUSCHAK	
Inventor's Signature		Date	
Residence: City Dayton	State NJ	Country USA	Citizenship U.S.A.
Mailing Address 1 Kings Road			
City Dayton	State NJ	ZIP 08810	Country U.S.A.
I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.			
NAME OF THIRD INVENTOR:		☐ A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any)) RAYMOND J		Family Name or Surname HULL, JR	
Inventor's Signature		Date	
Residence: City Hampton	State NJ	Country USA	Citizenship U.S.A.
Mailing Address 408 Rick Road			
City Hampton	State NJ	ZIP 08827	Country U.S.A.

115

110

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.			
NAME OF FOURTH INVENTOR:		☐ A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any]) JOHN		Family Name or Surname ORENGA	
Inventor's Signature		Date	
Residence: City Doylestown	State PA	Country USA	Citizenship U.S.A.
Mailing Address 4964 Davis Drive			
City Doylestown	State PA	ZIP 18901	Country U.S.A.

116
111

25. The system according to claim 16, wherein said first temperature is about 250° F and said second temperature is about 300° F.

5 26. The system according to claim 16, wherein said adhesive applicator is structured and arranged to apply said adhesive to said substrate at a rate of about 45 gsm to about 80 gsm.

10 27. The system according to claim 16, wherein said second pressure is in the range of about 50 psi to about 500 psi.

11/2

Abstract

A method and system for applying an adhesive/superabsorbent mixture to a substrate, the method and system being adapted for heating an adhesive and superabsorbent polymer mixture to a first temperature at a first pressure, the first
5 temperature being less than the boiling temperature of said mixture at the first pressure; heating the mixture through a heat exchanger at a second pressure, the second pressure being higher than the first pressure, the heat exchanger being adapted to raise the temperature of the mixture to a second temperature that is higher than the first temperature; and selectively applying the mixture to a substrate.




FIG. 1
(Prior Art)

BEST AVAILABLE COPY




FIG. 2

BEST AVAILABLE COPY