

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

05 March 2020 (05.03.2020)



(10) International Publication Number

WO 2020/046787 A1

(51) International Patent Classification:

C08L 23/08 (2006.01)

C08K 3/22 (2006.01)

D01F 8/06 (2006.01)

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(21) International Application Number:

PCT/US2019/048091

(22) International Filing Date:

26 August 2019 (26.08.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/725,367

31 August 2018 (31.08.2018)

US

(71) Applicant: DOW GLOBAL TECHNOLOGIES LLC

[US/US]; 2040 Dow Center, Midland, Michigan 48674 (US).

(72) Inventors: MATTUECCI, Scott T.; 633 Washington

Street, Building 1776, Midland, Michigan 48674 (US).

BONEKAMP, Jeffrey E.; 1501 Larkin Center Drive, Mid-

land, Michigan 48674 (US). KRASOVSKIY, Arkady L.;

230 Abner Jackson Parkway, Lake Jackson, Texas 77566

(US). SUN, Kefu; 230 Abner Jackson Parkway, Lake Jack-

son, Texas 77566 (US). LU, Keran; 230 Abner Jackson

Parkway, Lake Jackson, Texas 77566 (US). WEVERS,

Ronald; Herbert H. Dowweg 5, 4542 NM Hoek, Postbus

48, 4530 AA Terneuzen (NL).

(74) Agent: BARTHEL, Ted J.; Quarles & Brady LLP, 411

East Wisconsin Avenue, Suite 2400, Milwaukee, Wiscon-

sin 53202 (US).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,

DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,

HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,

KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,

MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,

OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,

SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,

TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH,

GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,

UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,

TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,

EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,

MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

(54) Title: FIBER WITH ODOR CONTROL COMPONENT

(57) Abstract: The present disclosure provides a fiber and fabrics made therefrom. In an embodiment, a fiber is provided and includes an odor control composition. The odor control composition includes (A) from 85 wt% to 99.5 wt% of an olefin-based polymer and (B) from 15 wt% to 0.5 wt% of an odor suppressant. The odor suppressant includes: (i) an ionomer, (ii) particles of zinc oxide, and (iii) particles of copper oxide.

WO 2020/046787 A1

FIBER WITH ODOR CONTROL COMPONENT

BACKGROUND

[0001] Hygiene articles, such as incontinence garments, feminine care products, and diapers require a high degree of odor control. Many such hygiene articles include fibers and/or fabric components for moisture absorption and/or odor control.

[0002] Odor control particles such as zeolites, sodium bicarbonate, activated silica, activated carbon, and metal oxides (such as zinc oxide (ZnO)), and zinc salts in particular, are known to consume many odor-generating molecules such as urea (and other amino-based odorants), H₂S and mercaptans that are typically arise during use of a hygiene article. All other factors being equal, it is known that ZnO concentration, for example, and odor suppression are directly related—*i.e.*, as ZnO concentration increases in a given olefin-based polymer article, the effectiveness of odor suppression also increases.

[0003] Although odor suppression increases as metal oxide (ZnO in particular) increases, limits do exist for the amount of ZnO that can be effectively incorporated into olefin-based polymer structures such as films and fibers. High loading of ZnO particles in polymeric films increases extrusion die lip buildup, thereby causing film defects. High loading of ZnO particles also increases haze, resulting in degradation of olefin-based polymer film transparency and/or degradation in film color. High loading of ZnO particles also deleteriously impacts mechanical properties such as impact strength and film tear strength. Processing parameters and end-use mechanical requirements thereby impose practical limits to the load of odor absorbers, such as ZnO particles, into olefin-based polymer compositions.

[0004] The art recognizes the on-going need for new odor control formulations for fiber and fabric structures. Further recognized in the art is the need for new odor control compositions for fibers and fabrics with suitable processing and mechanical properties for hygiene articles.

SUMMARY

[0005] The present disclosure provides a fiber. In an embodiment, a fiber is provided and includes an odor control composition. The odor control composition includes (A) from 85 wt% to 99.5 wt% of an olefin-based polymer and (B) from 15 wt% to 0.5 wt% of an odor

suppressant. The odor suppressant includes: (i) an ionomer, (ii) particles of zinc oxide, and (iii) particles of copper oxide.

[0006] The present disclosure provides a fabric. In an embodiment, a fabric is provided and includes a plurality of fibers. The fibers include (A) from 85 wt% to 99.5 wt% of an olefin-based polymer and (B) from 15 wt% to 0.5 wt% of an odor suppressant. The odor suppressant includes a blend of: (i) an ionomer, (ii) particles of zinc oxide, and (iii) particles of copper oxide.

DEFINITIONS

[0007] Any reference to the Periodic Table of Elements is that as published by CRC Press, Inc., 1990–1991. Reference to a group of elements in this table is by the new notation for numbering groups.

[0008] For purposes of United States patent practice, the contents of any referenced patent, patent application or publication are incorporated by reference in their entirety (or its equivalent U.S. version is so incorporated by reference) especially with respect to the disclosure of definitions (to the extent not inconsistent with any definitions specifically provided in this disclosure) and general knowledge in the art.

[0009] The numerical ranges disclosed herein include all values from, and including, the lower and upper value. For ranges containing explicit values (e.g., 1 or 2, or 3 to 5, or 6, or 7), any subrange between any two explicit values is included (e.g., the range 1-7 above includes subranges of 1 to 2; 2 to 6; 5 to 7; 3 to 7; 5 to 6; etc.).

[0010] Unless stated to the contrary, implicit from the context, or customary in the art, all parts and percents are based on weight and all test methods are current as of the filing date of this disclosure.

[0011] An "agglomerate" is a plurality of individual fine solid particles clumped or otherwise together forming a single mass.

[0012] The terms "blend" or "polymer blend," as used herein, is a blend of two or more polymers. Such a blend may or may not be miscible (not phase separated at molecular level). Such a blend may or may not be phase separated. Such a blend may or may not contain one or

more domain configurations, as determined from transmission electron spectroscopy, light scattering, x-ray scattering, and other methods known in the art.

[0013] The term "composition" refers to a mixture of materials which comprise the composition, as well as reaction products and decomposition products formed from the materials of the composition.

[0014] The terms "comprising," "including," "having" and their derivatives, are not intended to exclude the presence of any additional component, step or procedure, whether or not the same is specifically disclosed. In order to avoid any doubt, all compositions claimed through use of the term "comprising" may include any additional additive, adjuvant, or compound, whether polymeric or otherwise, unless stated to the contrary. In contrast, the term "consisting essentially of" excludes from the scope of any succeeding recitation any other component, step, or procedure, excepting those that are not essential to operability. The term "consisting of" excludes any component, step, or procedure not specifically delineated or listed. The term "or," unless stated otherwise, refers to the listed members individually as well as in any combination. Use of the singular includes use of the plural and vice versa.

[0015] An "ethylene-based polymer" is a polymer that contains more than 50 weight percent (wt%) polymerized ethylene monomer (based on the total amount of polymerizable monomers) and, optionally, may contain at least one comonomer. Ethylene-based polymer includes ethylene homopolymer, and ethylene copolymer (meaning units derived from ethylene and one or more comonomers). The terms "ethylene-based polymer" and "polyethylene" may be used interchangeably. Non-limiting examples of ethylene-based polymer (polyethylene) include low density polyethylene (LDPE) and linear polyethylene. Non-limiting examples of linear polyethylene include linear low density polyethylene (LLDPE), ultra-low density polyethylene (ULDPE), very low density polyethylene (VLDPE), multi-component ethylene-based copolymer (EPE), ethylene/ α -olefin multi-block copolymers (also known as olefin block copolymer (OBC)), substantially linear, or linear, plastomers/elastomers, and high density polyethylene (HDPE). Generally, polyethylene may be produced in gas-phase, fluidized bed reactors, liquid phase slurry process reactors, or liquid phase solution process reactors, using a heterogeneous catalyst system, such as Ziegler-Natta catalyst, a homogeneous catalyst system, comprising Group 4

transition metals and ligand structures such as metallocene, non-metallocene metal-centered, heteroaryl, heterovalent aryloxyether, phosphinimine, and others. Combinations of heterogeneous and/or homogeneous catalysts also may be used in either single reactor or dual reactor configurations.

[0016] "Ethylene plastomers/elastomers" are substantially linear, or linear, ethylene/ α -olefin copolymers containing homogeneous short-chain branching distribution comprising units derived from ethylene and units derived from at least one C_3 – C_{10} α -olefin comonomer. Ethylene plastomers/elastomers have a density from 0.870 g/cc to 0.917 g/cc. Non-limiting examples of ethylene plastomers/elastomers include AFFINITY™ plastomers and elastomers (available from The Dow Chemical Company), EXACT™ Plastomers (available from ExxonMobil Chemical), Tafmer™ (available from Mitsui), Nexlene™ (available from SK Chemicals Co.), and Lucene™ (available LG Chem Ltd.).

[0017] "High density polyethylene" (or "HDPE") is an ethylene homopolymer or an ethylene/ α -olefin copolymer with at least one C_4 – C_{10} α -olefin comonomer, or C_4 – C_8 α -olefin comonomer and a density from 0.940 g/cc, or 0.945 g/cc, or 0.950 g/cc, 0.953 g/cc to 0.955 g/cc, or 0.960 g/cc, or 0.965 g/cc, or 0.970 g/cc, or 0.975 g/cc, or 0.980 g/cc. The HDPE can be a monomodal copolymer or a multimodal copolymer. A "monomodal ethylene copolymer" is an ethylene/ C_4 – C_{10} α -olefin copolymer that has one distinct peak in a gel permeation chromatography (GPC) showing the molecular weight distribution. A "multimodal ethylene copolymer" is an ethylene/ C_4 – C_{10} α -olefin copolymer that has at least two distinct peaks in a GPC showing the molecular weight distribution. Multimodal includes copolymer having two peaks (bimodal) as well as copolymer having more than two peaks. Non-limiting examples of HDPE include DOW™ High Density Polyethylene (HDPE) Resins (available from The Dow Chemical Company), ELITE™ Enhanced Polyethylene Resins (available from The Dow Chemical Company), CONTINUUM™ Bimodal Polyethylene Resins (available from The Dow Chemical Company), LUPOLEN™ (available from Lyondell-Basell), as well as HDPE products from Borealis, Ineos, and ExxonMobil.

[0018] An "interpolymer" is a polymer prepared by the polymerization of at least two different monomers. This generic term includes copolymers, usually employed to refer to

polymers prepared from two different monomers, and polymers prepared from more than two different monomers, e.g., terpolymers, tetrapolymers, etc.

[0019] "Linear low density polyethylene" (or "LLDPE") is a linear ethylene/ α -olefin copolymer containing heterogeneous short-chain branching distribution comprising units derived from ethylene and units derived from at least one C_3 – C_{10} α -olefin, or C_4 – C_8 α -olefin, comonomer. LLDPE is characterized by little, if any, long chain branching, in contrast to conventional LDPE. LLDPE has a density from 0.910 g/cc to less than 0.940 g/cc. Non-limiting examples of LLDPE include TUFLIN™ linear low density polyethylene resins (available from The Dow Chemical Company), DOWLEX™ polyethylene resins (available from the Dow Chemical Company), and MARLEX™ polyethylene (available from Chevron Phillips).

[0020] "Low density polyethylene" (or "LDPE") consists of ethylene homopolymer, or ethylene/ α -olefin copolymer comprising at least one C_3 – C_{10} α -olefin, or C_4 – C_8 α -olefin, that has a density from 0.915 g/cc to less than 0.940 g/cc and contains long chain branching with broad MWD. LDPE is typically produced by way of high pressure free radical polymerization (tubular reactor or autoclave with free radical initiator). Non-limiting examples of LDPE include MarFlex™ (Chevron Phillips), LUPOLEN™ (LyondellBasell), as well as LDPE products from Borealis, Ineos, ExxonMobil, and others.

[0021] "Multi-component ethylene-based copolymer" (or "EPE") comprises units derived from ethylene and units derived from at least one C_3 – C_{10} α -olefin, or C_4 – C_8 α -olefin, comonomer, such as described in patent references USP 6,111,023; USP 5,677,383; and USP 6,984,695. EPE resins have a density from 0.905 g/cc to 0.962 g/cc. Non-limiting examples of EPE resins include ELITE™ enhanced polyethylene (available from The Dow Chemical Company), ELITE AT™ advanced technology resins (available from The Dow Chemical Company), SURPASS™ Polyethylene (PE) Resins (available from Nova Chemicals), and SMART™ (available from SK Chemicals Co.).

[0022] An "olefin-based polymer" or "polyolefin" is a polymer that contains more than 50 weight percent polymerized olefin monomer (based on total amount of polymerizable monomers), and optionally, may contain at least one comonomer. Non-limiting examples of an olefin-based polymer include ethylene-based polymer or propylene-based polymer.

[0023] A "polymer" is a compound prepared by polymerizing monomers, whether of the same or a different type, that in polymerized form provide the multiple and/or repeating "units" or "mer units" that make up a polymer. The generic term polymer thus embraces the term homopolymer, usually employed to refer to polymers prepared from only one type of monomer, and the term copolymer, usually employed to refer to polymers prepared from at least two types of monomers. It also embraces all forms of copolymer, e.g., random, block, etc. The terms "ethylene/ α -olefin polymer" and "propylene/ α -olefin polymer" are indicative of copolymer as described above prepared from polymerizing ethylene or propylene respectively and one or more additional, polymerizable α -olefin monomer. It is noted that although a polymer is often referred to as being "made of" one or more specified monomers, "based on" a specified monomer or monomer type, "containing" a specified monomer content, or the like, in this context the term "monomer" is understood to be referring to the polymerized remnant of the specified monomer and not to the unpolymerized species. In general, polymers herein are referred to as being based on "units" that are the polymerized form of a corresponding monomer.

[0024] A "propylene-based polymer" is a polymer that contains more than 50 weight percent polymerized propylene monomer (based on the total amount of polymerizable monomers) and, optionally, may contain at least one comonomer. Propylene-based polymer includes propylene homopolymer, and propylene copolymer (meaning units derived from propylene and one or more comonomers). The terms "propylene-based polymer" and "polypropylene" may be used interchangeably. Non-limiting examples of suitable propylene copolymer include propylene impact copolymer and propylene random copolymer.

[0025] "Ultra-low density polyethylene" (or "ULDPE") and "very low density polyethylene" (or "VLDPE") each is a linear ethylene/ α -olefin copolymer containing heterogeneous short-chain branching distribution comprising units derived from ethylene and units derived from at least one C_3 – C_{10} α -olefin comonomer. ULDPE and VLDPE each has a density from 0.885 g/cc to 0.915 g/cc. Non-limiting examples of ULDPE and VLDPE include ATTANE™ ultra low density polyethylene resins (available from The Dow Chemical Company) and FLEXOMER™ very low density polyethylene resins (available from The Dow Chemical Company).

TEST METHODS

[0026] D10, D50, and D90 particle size is measured using a Coulter LS 230 Laser Light Scattering Particle Sizer, available from Coulter Corporation. D10 particle size is the particle diameter at which 10% of the powder's mass is composed of particles with a diameter less than this value. D50 particle size is the particle diameter at which 50% of the powder's mass is composed of particles with a diameter less than this value and 50% of the powder's mass is composed of particles with a diameter greater than said value. D90 particle size is the particle diameter at which 90% of the powder's mass is composed of particles with a diameter less than this value. Mean volume average particle size is measured using a Coulter LS 230 Laser Light Scattering Particle Sizer, available from Coulter Corporation. Particle size distribution is calculated in accordance with Equation A:

$$\text{Particle size distribution} = \frac{(D90-D10)}{D50} \quad \text{Equation A.}$$

[0027] Dart impact strength is measured in accordance with ASTM D1709, with results reported in grams (g).

[0028] Denier is a unit of measure for the linear mass density of fibers, with units of g/9000m of fiber.

[0029] Density is measured in accordance with ASTM D792, Method B. The result is recorded in grams per cubic centimeter (g/cc).

[0030] Differential Scanning Calorimetry (DSC). Differential Scanning Calorimetry (DSC) can be used to measure the melting, crystallization, and glass transition behavior of a polymer over a wide range of temperature. For example, the TA Instruments Q1000 DSC, equipped with an RCS (refrigerated cooling system) and an autosampler is used to perform this analysis. During testing, a nitrogen purge gas flow of 50 ml/min is used. Each sample is melt pressed into a thin film at about 175°C; the melted sample is then air-cooled to room temperature (about 25°C). A 3–10 mg, 6 mm diameter specimen is extracted from the cooled polymer, weighed, placed in a light aluminum pan (ca 50 mg), and crimped shut. Analysis is then performed to determine its thermal properties.

[0031] The thermal behavior of the sample is determined by ramping the sample temperature up and down to create a heat flow versus temperature profile. First, the sample is

rapidly heated to 180°C and held isothermal for 3 minutes in order to remove its thermal history. Next, the sample is cooled to -40°C at a 10°C/minute cooling rate and held isothermal at -40°C for 3 minutes. The sample is then heated to 180°C (this is the "second heat" ramp) at a 10°C/minute heating rate. The cooling and second heating curves are recorded. The cool curve is analyzed by setting baseline endpoints from the beginning of crystallization to -20°C. The heat curve is analyzed by setting baseline endpoints from -20°C to the end of melt. The values determined are extrapolated onset of melting, T_m , and extrapolated onset of crystallization, T_c . Heat of fusion (H_f) (in Joules per gram), and the calculated % crystallinity for polyethylene samples using the following Equation: $\% \text{ Crystallinity} = ((H_f)/292 \text{ J/g}) \times 100$. Glass transition temperature, T_g , is determined from the DSC heating curve where half the sample has gained the liquid heat capacity as described in Bernhard Wunderlich, *The Basis of Thermal Analysis, in Thermal Characterization of Polymeric Materials* 92, 278–279 (Edith A. Turi ed., 2d ed. 1997). Baselines are drawn from below and above the glass transition region and extrapolated through the T_g region. The temperature at which the sample heat capacity is half-way between these baselines is the T_g .

[0032] Elmendorf tear (or tear) is measured in accordance with ASTM D1922-15, machine direction (MD), with results reported in grams-force (gf).

[0033] Melt flow rate (MFR) in g/10 min is measured in accordance with ASTM D1238 (230°C/2.16 kg).

[0034] Melt index (MI) (I2) in g/10 min is measured in accordance with ASTM D1238 (190°C/2.16 kg).

[0035] Odor Suppression /Odor Suppression Value.

[0036] Odor suppression is the ability of a composition to neutralize, or otherwise reduce, the amount of volatile sulfur-containing compounds. In the present disclosure, the odor suppression for methyl mercaptan is measured with gas chromatography equipped with an Agilent Sulfur Chemiluminescence Detector (GC-SCD) in accordance with ASTM D5504-12. A control sample is prepared by placing a film formed from DOWLEX™ 2085G, ethylene/octene LLDPE, into a Tedlar® bag (polyvinyl fluoride). The Tedlar® bag for the control is subsequently filled with 900 mL of helium gas and known amounts of methyl

mercaptan, and the Tedlar® bag is closed. Test samples are prepared by placing a film formed from respective test compositions, each test film placed into a respective Tedlar® bag. Each Tedlar® bag is subsequently filled with 900 mL of helium gas and known amount of methyl mercaptan, and the Tedlar® bag is closed. Samples are injected onto the GC-SCD at pre-determined time intervals from each bag in order to evaluate odor suppression capability.

[0037] The reference samples and test samples were analyzed after two days. The reference sample was used as the calibration standard to calculate the methyl mercaptan concentration of each test sample.

[0038] A. Sample Preparation

[0039] The control sample and each test sample containing 5 ppmv methyl mercaptan were prepared in SKC 1 L sample bag (SKC Tedlar® Sample Bag, 1 Liter, Cat No. 232-01). A reference sample without a film was prepared in a Tedlar® bag as the calibration standard.

1. Cut 1.0 g of film into strips (approximately 1 cm x 30 cm).
2. Unscrew the valve from the sample bag, insert the film strips into the bag through the valve opening with the handle of cotton tipped applicator, and install the valve back to the sample bag, squeeze air out of bag before tightening the valve to seal the bag.
3. Fill the bag with 0.90 L of helium gas (AirGas, Ultra Grade Helium).
4. Inject 50 mL of 100 ppmv methyl mercaptan, into the bag using a gas-tight glass syringe.

[0040] The odor suppression value test can also be performed for other odorants, including ethyl mercaptan, propyl mercaptan, and butyl mercaptan.

[0041] B. GC-SCD Conditions

- 1 Gas chromatograph: Agilent Model 7890 with a split/splitless injection port, available from Agilent Technologies, 2850 Centerville Road, Wilmington, DE 19808.
2. Detector: Agilent Sulfur Chemiluminescence (SCD), Model G6644A.
3. Chromatography data system: Agilent OpenLAB software.
4. Columns: Agilent J&W DB-1 30 m x 0.32 mm ID, 5 µm film thickness.
5. Carrier Gas: Hydrogen, constant flow mode, 2.0 mL/min.
6. Inlet: Split, temperature: 250 °C, split ratio: 100:1.
7. Injection volume: 500 µL by Valco Six Port Valve, Loop Size: 500 µL.

8. Oven Temperature: 30 °C hold for 1 minute, 15 °C/min to 140 °C, hold for 1 minutes.

9. SCD Detector Conditions:

Temperature: 250 °C.

Hydrogen Flow: 38.3 mL/min.

Oxidizer Flow: 59.9 sccm.

Pressure: 400 Torr.

An odor suppression value (OSV) is the removal% of methyl mercaptan calculated by the following equation:

$$\begin{aligned} \text{OSV} &= \frac{\text{Concentration of Reference Sample} - \text{Concentration of Test Sample}}{\text{Concentration of Reference Sample}} \times 100 \\ &= \frac{\text{Peak Area of Reference Sample} - \text{Peak Area of Test Sample}}{\text{Peak Area of Reference Sample}} \times 100 \end{aligned}$$

The Peak Area is the response of GC-SCD.

[0042] A non-limiting example of OSV calculation is provided. At two days the GC-SCD peak area of methylmercaptan in the reference sample is 28240298, whereas the GC-SCD peak area of methyl mercaptan in the test sample IE 1 is 5667327 (unit is pA*s in Agilent OpenLAB software). The odor suppression value for the test sample IE 1 is $((28240298 - 5667327)/28240298) \times 100 = 80$. As shown in the equation of OSV, both concentration of methyl mercaptan and GC-SCD Peak Area of methyl mercaptan can be used to calculate OSV.

[0043] Porosity and Surface Area. Brunauer–Emmett–Teller (BET) porosity and surface area analysis are performed using a Micromeritics Accelerated Surface Area & Porosimetry instrument (ASAP 2420). The sample is out-gassed at 105°C while under vacuum prior to analysis.

[0044] The ASAP 2420 instrument employs a static (volumetric) method of dosing samples and measures the quantity of gas that can be physically adsorbed (physisorbed) on a solid at liquid nitrogen temperature. For the multi-point BET measurement the volume of nitrogen uptake is measured at pre-selected relative pressure points at constant temperature. The relative pressure is the ratio of the applied nitrogen pressure to the vapor pressure of nitrogen at the analysis temperature of 77 Kelvin (K). Results for porosity are reported in cubic meters per gram, or m³/g. Results for surface area are reported in square

meters per gram, or m^2/g .

[0045] The term “ramp-to-break” refers to the drawing speed, in meters per minute (or mpm), at which the fiber completely breaks down and is discontinuous. Ramp-to-break is a method for determining the maximum line speed for drawing down fibers on the Hills line as achieved by gradually increasing the take up speed of the filament bundle. This is accomplished with a ramping method to a point where at least one fiber break occurs. The highest speed that a material can be run for a minimum of 30 seconds without a single fiber break is the maximum draw down speed or ramp-to-break speed. The ramping procedure starts at 1500 mpm winding speed – or lower, if necessary. The material is run at this line speed for 30 seconds and if no fiber breaks are observed then the godet roll speed is increased by 250 mpm over 30 seconds. The material is run for 30 seconds at each interim point while checking for breaks. This is done until a break is achieved. The speed at which the break occurs is recorded. The process is repeated a minimum of three times and the average is recorded as the maximum draw down speed via the ramp-to-break methodology. The standard deviation for repeat measurements on the same polymer is ca 100 mpm.

[0046] The term “tenacity” refers to the ratio of load required to break a fiber and the denier of the fiber, measured in accordance with ASTM D3217-07.

[0047] The term “tensile strength” refers to the maximum amount of tensile stress that a fiber can withstand before breaking, measured in accordance with ASTM D76M-11(2016).

[0048] Zinc/copper—total amount. The total amount of zinc and/or copper present in a composition is determined with x-ray fluorescence spectrometry (XRS), in accordance with ASTM D6247. Results are reported in parts per million, or ppm.

DETAILED DESCRIPTION

[0049] The present disclosure provides a fiber. In an embodiment, a fiber is provided and includes an odor control composition. The odor control composition includes: (A) from 85 wt% to 99.5 wt% of an olefin-based polymer, and (B) from 15 wt% to 0.5 wt% of an odor suppressant comprising a blend of: (i) an ionomer; (ii) particles of zinc oxide; and (iii) particles of copper oxide.

[0050] Fiber

[0051] A “fiber” is a single, continuous strand of elongated material having a generally

round cross-section and a length to diameter ratio of greater than 10.

[0052] Odor Control Composition

[0053] The present fiber includes an odor control composition. In an embodiment, the odor control composition includes from 85 wt%, or 90 wt% to 95 wt%, or 97 wt%, 99 wt%, or 99.5 wt% component (A) that is an olefin-based polymer. The odor control composition includes a reciprocal amount of component (B), or from 15 wt%, or 10 wt% to 5 wt%, or 3 wt%, 1 wt% or 0.5 wt% of an odor suppressant.

[0054] The odor control composition has an odor suppression value from 45%, or 46%, or 50%, or 60%, or 70% to 75%, or 80%, or 85%, or 90%, as measured in accordance with ASTM D5504-12.

[0055] A. Olefin-based polymer

[0056] The present composition includes an olefin-based polymer. The olefin-based polymer can be a propylene-based polymer or an ethylene-based polymer. Non-limiting examples of propylene-based polymer include propylene copolymer, propylene homopolymer, and combinations thereof. In an embodiment, the propylene-based polymer is a propylene/ α -olefin copolymer. Non-limiting examples of suitable α -olefins include C_2 and C_4 – C_{20} α -olefins, or C_4 – C_{10} α -olefins, or C_4 – C_8 α -olefins. Representative α -olefins include ethylene, 1-butene, 1-pentene, 1-hexene, 1-heptene and 1-octene.

[0057] In an embodiment, the propylene/ α -olefin copolymer is a propylene/ethylene copolymer containing greater than 50 wt% units derived from propylene, or from 51 wt%, or 55 wt%, or 60 wt% to 70 wt%, or 80 wt%, or 90 wt%, or 95 wt%, or 99 wt% units derived from propylene, based on the weight of the propylene/ethylene copolymer. The propylene/ethylene copolymer contains a reciprocal amount of units derived from ethylene, or from less than 50 wt%, or 49 wt%, or 45 wt%, or 40 wt% to 30 wt%, or 20 wt%, or 10 wt%, or 5 wt%, or 1 wt% units derived from ethylene, based on the weight of the propylene/ethylene copolymer.

[0058] In an embodiment, the olefin-based polymer is an ethylene-based polymer. The ethylene-based polymer can be an ethylene homopolymer or an ethylene/ α -olefin copolymer.

[0059] In an embodiment, the ethylene-based polymer is an ethylene/ α -olefin copolymer. Non-limiting examples of suitable α -olefins include C_3 – C_{20} α -olefins, or C_4 – C_{10} α -

olefins, or C₄–C₈ α-olefins. Representative α-olefins include propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene and 1-octene.

[0060] In an embodiment, the ethylene/α-olefin copolymer is an LLDPE that is an ethylene/C₄–C₈ α-olefin copolymer. The LLDPE has one, some, or all of the following properties:

[0061] (i) a density from 0.910 g/cc to 0.930 g/cc, or from 0.915 g/cc to 0.926 g/cc; and/or

[0062] (ii) a melt index from 0.5 g/10 min, or 1.0 g/10min, or 2.0 g/10min to 3.0 g/10min, or 4.0 g/10min, or 5.0 g/10min.

B. Odor suppressant

[0063] The present composition includes an odor suppressant. The odor suppressant is composed of a (Bi) an ionomer, (Bii) particles of zinc oxide, and (Biii) particles of copper oxide.

[0064] (Bi) Ionomer

[0065] The present composition includes an ionomer. An “ionomer,” as used herein, is an ion-containing polymer. An “ion” is an atom that has an electrical charge, either positive or negative. The ionomer has a majority weight percent (generally 85% to 90%) of repeating monomer units that are non-ionic (non-polar), and a minority weight percent (generally 10% to 15%) of repeating comonomer units that are ionic, or polar (*i.e.*, positively-charged or negatively-charged). The positive charges of the ionic groups attract the negative charges of the ionic groups, creating ionic bonds. Ionomer resins exhibit what is known as “reversible crosslinking” behavior, *i.e.* when an ionomer is heated, the polymer chains have increased mobility, and the ionic bonds cannot stay intact because the positive charges and negative charges are pulled away from each other.

[0066] Non-limiting examples of the monomers and comonomers from which an ionomer is derived include a copolymer of at least one alpha-olefin and at least one ethylenically unsaturated carboxylic acid and/or anhydride. Non-limiting examples of suitable alpha-olefins include ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, and 3-methylbutene. Non-limiting examples of suitable carboxylic acids and anhydrides include acrylic acid, methacrylic acid, ethacrylic acid, maleic acid, fumaric acid, and maleic anhydride.

[0067] In an embodiment, the ionomer is a copolymer of ethylene and methacrylic acid.

[0068] In an embodiment, the ionomer is a copolymer of ethylene and acrylic acid.

[0069] In an embodiment, the ionomer is a metal ionomer. A "metal ionomer," as used herein, refers to a copolymer based on a metal salt of a copolymer of an alpha-olefin and an ethylenically unsaturated carboxylic acid and/or anhydride. The metal ionomer may be fully or partially neutralized by a metal ion. Non-limiting examples of metals suitable for neutralizing an ionomer include the alkali metals, *i.e.*, cations such as sodium, lithium, and potassium; alkaline earth metals, *i.e.*, cations such as calcium, magnesium; and transition metals such as zinc. A non-limiting example of a metal ionomer is Surlyn® 8660, which is a sodium salt of an ethylene and methacrylic acid copolymer, available from Dow-DuPont.

[0070] In an embodiment, the metal ionomer is a zinc ionomer. The term "zinc ionomer," (or "ZnI/O") as used herein, refers to a copolymer based on a zinc salt of a copolymer of ethylene and a vinyl comonomer with carboxylic acid/or anhydride. Non-limiting examples of suitable comonomer having vinyl comonomer with an acid group include methyl/methacrylic acid, vinyl acrylic acid, methacrylate, n-butyl acrylic acid, and acrylic acid.

[0071] Non-limiting examples of suitable zinc ionomer include zinc salt of ethylene/acrylic acid comonomer, zinc salt of ethylene/methyl-methacrylic acid copolymer, zinc salt of ethylene/vinyl acrylic acid copolymer, zinc salt of ethylene/methacrylate copolymer, zinc salt of ethylene/n-butyl acrylic acid copolymer, and any combination thereof.

[0072] In an embodiment, the zinc ionomer is a zinc salt of ethylene/acrylic acid copolymer. Non-limiting examples of a suitable zinc ionomer include Surlyn® 9150, which is a zinc salt of an ethylene and methacrylic acid copolymer, available from Dow-DuPont.

[0073] B(ii) Particles of Zinc Oxide

[0074] The odor suppressant includes particles of zinc oxide (or "ZnO"). The ZnO particles have a D50 particle size from 100 nm to 3000 nm, a surface area from 1 m²/g to less than 10 m²/g, and a porosity less than 0.020 m³/g.

[0075] In an embodiment, the ZnO particles have one, some, or all of the following properties (i)-(iii) below:

[0076] (i) a particle size D50 from 100 nm, or 200 nm, or 300 nm, or 400 nm to 500 nm, or 600 nm, or 700 nm, or 800 nm, or 900 nm, or 1000 nm, or 2000 nm, or 3000 nm; and/or

[0077] (ii) a surface area from 1 m²/g, or 2 m²/g, or 3 m²/g, or 4 m²/g to 5 m²/g, or 6 m²/g, or 7 m²/g, or 8 m²/g, or 9 m²/g; and/or

[0078] (iii) a porosity from 0.005 m³/g, or 0.006 m³/g, or 0.008 m³/g, or 0.010 m³/g to 0.012 m³/g, or 0.013 m³/g, or 0.015 m³/g, or less than 0.020 m³/g.

[0079] Non-limiting examples of suitable ZnO particles include 800HSA (Zinc Oxide, LLC), ZnO micropowder (US Research Nanomaterials), and Zoco102 (Zochem, Inc.).

[0080] (Biii) Particles of Copper Oxide

[0081] The odor suppressant also includes particles of copper oxide. The copper oxide can be either “Cu₂O” (copper I oxide) or “CuO” (copper II oxide), or a mix of both. In an embodiment, the copper oxide particles have a D50 particle size from 100 nm to 3000 nm and a surface area from 1 m²/g to less than 10 m²/g. Bounded by no particular theory, it is believed that the copper oxide particles contribute as a sulfur scavenger for hydrogen sulfide and mercaptans in particular.

[0082] In an embodiment, the copper oxide particles have a particle size D50 from 100 nm, or 200 nm, or 300 nm, or 400 nm to 500 nm, or 600 nm, or 700 nm, or 800 nm, or 900 nm, or 1000 nm, or 2000 nm, or 3000 nm. Non-limiting examples of suitable copper oxide particles include Cu₂O 325 mesh powder and CuO 325 mesh powder available from Reade Advanced Materials.

C. Composition

[0083] The present composition includes (A) from 85 wt% to 99.5 wt% of the olefin-based polymer and (B) from 15 wt% to 0.5 wt% of the odor suppressant, based on total weight of the composition (hereafter, *Composition 1*). The odor suppressant is mixed, or otherwise blended, into the olefin-based polymer matrix, and is a blend of (Bi) an ionomer, (Bii) particles of zinc oxide, and (Biii) particles of copper oxide. The composition has an odor suppression value of greater than 45%. In an embodiment, the composition has an odor suppression value from 46%, or 49%, or 50% or 60% or 70% to 75%, or 80%, or 85%, or 90%.

[0084] The ZnI/O (Bi) is present in component (B) in an amount of 1 to 90 wt% based on the total weight of component (B). The ratio of ZnO to ZnI/O (hereafter “ZnO to ZnI/O ratio”)

is from 3:1 to 1:7 based on the total weight of the odor suppressant (B). The ZnO to ZnI/O ratio can be from 3:1, or 2:1, or 1:1 to 1:2, or 1:3, or 1:4, or 1:5, or 1:6, or 1:7. The particles of copper oxide (Biii) are present in component (B) in an amount of from 0.01 wt% to 30 wt% based on the total weight of component (B). The particles of copper oxide can be copper (I) oxide (Cu_2O), copper (II) oxide (CuO), or a mix of both. In an embodiment, the weight percent ratio between the ionomer (Bi), the zinc oxide (Bii), and the copper oxide (Biii) is from 150:100:1 to 2.9:2.5:1 based on the total weight of the odor suppressant (B) (hereafter, *Composition 1*).

[0085] In an embodiment, the weight percent ratio between the ionomer (Bi), the zinc oxide (Bii), and the copper oxide (Biii) is from 100:75:1 to 3:2.5:1 based on the total weight of the odor suppressant (B).

[0086] In an embodiment, the present composition includes from 85 wt%, or 90 wt% to 95 wt%, or 97 wt%, 99 wt%, or 99.4 wt%, or 99.5 wt% component (A) that is an ethylene-based polymer. The present composition includes a reciprocal amount of the odor suppressant, component (B), or from 15 wt%, or 10 wt% to 5 wt%, or 3 wt%, 1 wt%, or 0.6 wt%, or 0.5 wt% odor suppressant wherein Zn I/O to ZnO to Cu_2O ratio is from 12.5:12.5:1 to 2.5:2.5:1. The odor suppressant (B) can be any odor suppressant as previously disclosed herein (hereafter, *Composition 2*).

[0087] The composition (*i.e. Composition 1 and/or Composition 2*) has an odor suppression value from 46%, or 50%, or 60%, or 70% to 75%, or 80%, or 85%, or 90%.

[0088] While the combination of ZnO and ionomer improve OSV for methyl mercaptan, the addition of copper oxide, and in particular Cu_2O , has been observed to further improve overall OSV. In fact, Applicant surprisingly discovered that the addition of from 0.01 wt% to 0.1 wt% of Cu_2O to a ZnO/ionomer odor suppressing composition (based on the total weight of odor suppressant composition (B), for example) can more than double the OSV performance compared to ZnO/ionomer odor suppressing compositions that lack the copper oxide particles.

D. Blend

[0089] Components (A) and (B) are mixed, or otherwise blended, together to form the present composition so that the particles of zinc oxide and the particles of copper oxide are (i) dispersed within the olefin-based polymer (A) and/or (i) dispersed within the ionomer (Bi).

[0090] In an embodiment, the present composition is produced as an odor control masterbatch wherein component (B) is formed by dispersing the zinc oxide particles (Bii) and the copper oxide particles (Biii) into the ionomer (Bi). The dispersing may be accomplished by physical mixing and/or melt blending of components (Bi), (Bii), and (Biii) in order to uniformly disperse the particles (zinc oxide and copper oxide) throughout the ionomer. The resultant component (B) is subsequently mixed, or otherwise blended, with the olefin-based polymer, component (A). The mixing of component (B) and component (A) may be accomplished by physical mixing and/or melt blending (hereafter *odor control masterbatch 1*).

[0091] In an embodiment, the present composition is produced as an odor control masterbatch by dispersing the zinc oxide particles (Bii) into the ionomer (Bi). The dispersing may be accomplished by physical mixing and/or melt blending of components (Bi) and (Bii) in order to uniformly disperse the zinc particles throughout the ionomer (Bi) (“Bi-Bii blend”). The Bi-Bii blend and the copper oxide particles are subsequently added to the olefin-based polymer component (A) by physical mixing and/or melt blending to form the present composition of a homogeneous blend of olefin-based polymer (A), ionomer (Bi), zinc oxide particles (Bii), and copper oxide particles (Biii). (hereafter *odor control masterbatch 2*)

[0092] In an embodiment, the present composition is produced as an odor control masterbatch by mixing the ionomer (Bi), the zinc oxide particles (Bii), the copper oxide particles (Biii) and the olefin-based polymer (A). The mixing may be accomplished by physical mixing and/or melt blending of components (A), (Bi), (Bii), and (Biii) in order to uniformly disperse the ionomer (Bi), the zinc oxide particles (Bii), and the copper oxide particles (Biii) throughout the olefin-based polymer (A) (hereafter *odor control masterbatch 3*).

[0093] In an embodiment, the present composition is produced as an odor control masterbatch by mixing the ionomer (Bi), the zinc oxide particles (Bii), and the olefin-based polymer (A). The mixing may be accomplished by physical mixing and/or melt blending of components (Bi), (Bii), and (A) in order to uniformly disperse (Bi) and (Bii) throughout (A) (hereafter, *A-Bi-Bii blend*). Copper oxide particles (Biii) are mixed with component (A). The

mixing may be accomplished by physically mixing and/or melt blending in order to uniformly disperse the copper oxide particles (Biii) into (A) (hereafter, *A-Biii blend*). The *A-Bi-Bii blend* is then mixed with the *A-Biii blend*. The mixing may be accomplished by physical mixing and/or melt blending to form a homogeneous composition composed of olefin-based polymer (A), ionomer (Bi), zinc oxide particles (Bii), and copper oxide particles (Biii) (hereafter, *odor control masterbatch 4*).

[0094] In an embodiment, the odor control masterbatch (*i.e.*, any of *odor control masterbatch 1, 2, 3, or 4*) includes from 20 wt% to 30 wt% ionomer, from 20 wt% to 30 wt% particles of zinc oxide, from 5 wt% to 15 wt% particles of copper oxide, and from 30 wt% to 60 wt% LLDPE, with the aggregate of the components amounting to 100 wt% odor control composition.

[0095] The present fiber may be a mono-component fiber, a homofil fiber, or a bi-component fiber.

[0096] In an embodiment, the fiber is a mono-component fiber. A "mono-component fiber" (also known as "monofiber" or "homofil fiber") is a fiber that is a continuous strand of a single material. The mono-component fiber can have either an indefinite (*i.e.*, not predetermined) length, or a definite length (*i.e.*, a "staple fiber" which is a discontinuous strand of material which has been cut or otherwise divided into segments of a predetermined length). A mono-component fiber is a fiber that has a single polymer region or domain, and that does not have any other distinct polymer regions (as does a bi-component fiber).

[0097] In an embodiment, the fiber is a bi-component fiber. A "bi-component fiber" is a fiber that has two or more distinct polymeric components. Bi-component fibers are also known as conjugated or multicomponent fibers. The polymers are usually different from each other although two or more components may comprise the same polymer. The polymeric components are arranged in distinct zones across the cross-section of the bi-component fiber. The different components of the bi-component fiber usually extend continuously along the length of the bi-component fiber. The configuration of a bi-component fiber can be, for example, a sheath-core arrangement (in which one polymer is surrounded by another), a segmented pie arrangement, or an "islands-in-the sea" arrangement.

[0098] The bi-component fiber includes a first component and a second component, wherein the first component is the odor control composition.

[0099] Non-limiting examples of suitable materials for the second component include olefin-based polymer (*i.e.* propylene-based polymer and ethylene-based polymer), polyesters such as polyethylene terephthalate, glycol-modified polyethylene terephthalate, polybutylene terephthalate, polylactic acid, polytrimethylene terephthalate (*e.g.*, SORONA® available from DuPont), polyethylene 2,5-furandicarboxylate, polyhydroxybutyrate, polyamide, polylactic acid (*e.g.*, NatureWorks available from Cargill-Dow and LACEA® from Mistui Chemical), diacid/diol aliphatic polyester (*e.g.* BIONOLLE® 1000 and BIONELLE® 3000 available from Showa High Polymer Company, Ltd.), and aliphatic/aromatic copolyester (*e.g.* EASTAR™ BIO Copolyester from Eastman Chemical or ECOFLEX™ from BASF), and combinations thereof.

[0100] The polyester may have a density ranging from 1.2 g/cc to 1.5 g/cc, or from 1.35 g/cc to 1.45 g/cc.

[0101] The polyester may have a molecular weight equivalent to an intrinsic viscosity (IV) from 0.5 dl/g to 1.4 dl/g, as determined according to ASTM D4603 or ASTM D2857.

[0102] In an embodiment, the bi-component fiber has a sheath-core configuration whereby the core (composed of the second component) is either centrally or non-centrally located within the sheath (composed of the odor control composition), with the sheath completely surrounding the core.

[0103] In an embodiment, the bi-component fibers have a segmented pie configuration. The fiber is composed of a plurality of first pie segments. The first pie segments are composed of the first component that is the odor control composition. The fiber also includes a plurality of second pie segments. The second pie segments are composed of the second component. Each pie segment extends from a center point of the fiber and extends radially outward to the outer surface of the fiber. The volume of the fiber is filled by an alternating arrangement of first pie segments and second pie segments. The alternating first pie segments and second pie segments extend along the length, or along the entire length, of the fiber, and are integral and inseparable.

[0104] In an embodiment, the bi-component fibers have an “islands-in-the-sea

configuration.” The fiber is composed of a plurality of cores (formed from the second component). The plurality of cores are separated from each other and are disposed in a sheath composed of the first component that is the odor control composition. The plurality of cores form discrete “islands” within the “sea,” which is the sheath. The material of the sheath (the odor control composition, first component) separates the plurality of cores (second component) from each other. The material of the sheath also surrounds, or otherwise encases, the plurality of cores. The plurality cores (“islands”) and sheath (“sea”) extend along the length, or along the entire length, of the fiber, and are integral and inseparable.

[0105] The fiber (mono-component or bi-component) may be a melt-spun fiber or a meltblown fiber.

[0106] In an embodiment, the fiber (mono-component or bi-component) is a melt-spun fiber. A “melt-spun fiber,” as used herein, is a fiber produced by a melt-spinning process. Melt-spinning is a process whereby a polymer melt is extruded through a plurality of fine die capillaries (such as a spinnerette, for example) as molten filaments while simultaneously applying an extensional force which reduces the density of the molten filaments. The molten filaments solidify upon cooling below their melt temperature to form fibers. The term “melt spinning” encompasses staple fiber spinning (including short spinning and long spinning) and bulk continuous filament fiber. Melt-spun fibers may be cold-drawn.

[0107] In an embodiment, the fiber is a meltblown fiber. A “meltblown fiber” is a fiber formed by extruding a molten thermoplastic polymer composition through a plurality of fine, usually circular, die capillaries as molten threads or filaments into converging high velocity gas streams (e.g. air) which function to attenuate the threads or filaments to reduced density. The filaments or threads are carried by the high velocity gas streams and deposited on a collecting surface to form a web of randomly dispersed fibers with average thickness generally smaller than 10 microns.

[0108] In an embodiment, the fiber has a density with a lower limit of 15 denier and an upper limit of 100 denier.

[0109] In an embodiment, the fiber has a ramp-to-break from 2600 meters per minute (mpm) to 3200 mpm.

[0110] In an embodiment, the fiber has a tensile strength from 30 g/5cm, or 50 g/5cm to 100 g/5cm.

[0111] In an embodiment, the fiber has a tenacity of at least 2 cn/Tex.

[0112] The fiber may optionally include one or more other additives. Non-limiting examples of suitable additives include stabilizers, antioxidants, fillers, colorants, nucleating agents, mold release agents, dispersing agents, catalyst deactivator, UV light absorbent, flame retardant, coloring agent, mold release agent, lubricant, anti-static agent, pigment, and any combination of the foregoing.

[0113] The present fiber may comprise two or more embodiments disclosed herein.

[0114] Fabric

[0115] The present disclosure provides a fabric. In an embodiment, the fabric includes a plurality of fibers. The fibers include an odor control component. The odor control component includes: (A) from 85 wt% to 99.5 wt% of an olefin-based polymer and (B) from 15 wt% to 0.5 wt% of an odor suppressant. The odor suppressant is composed of a blend of: (i) an ionomer, (ii) particles of zinc oxide, and (iii) particles of copper oxide.

[0116] In an embodiment, the odor control composition has a methyl mercaptan odor suppression value of greater than 45% as measured in accordance with ASTM D5504-12.

[0117] A “fabric” is a woven structure or a non-woven structure formed from individual fibers or yarn.

[0118] A “woven fabric” is an assembly of interlaced fibers (or yarns). The woven fabric is fabricated by weaving two distinct sets of fibers—the warp fibers (or “warp”) and the weft fibers (or “weft”). The warp is the set of fibers in place in a loom before the weft is introduced. The weft is the set of fibers introduced during the weaving process. The lengthwise or longitudinal warp fibers are held stationary in tension on a frame or a loom while the transverse weft fibers are drawn through and inserted over-and-under the warp. The warp and the weft are interlaced at right angles to form the fabric. Non-limiting examples of interlaced woven fabric structures include lock-stitch knitted fabric.

[0119] As used herein a “non-woven” or a “non-woven fabric” or “non-woven material” is an assembly of fibers (for example, sheath-core, segmented pie, or “islands-in-the-sea”) held together in a random web such as by mechanical interlocking or by fusing at least a portion of the fibers. The non-woven fabrics according to the present disclosure may be fabricated via different techniques. Such methods include, but are not limited to, spunbond process, melt-blowing process, carded web process, air laid process, thermo-calendaring process, adhesive bonding process, hot air bonding process, needle punch process, hydroentangling process, electrospinning process, and combinations thereof.

[0120] In an embodiment, the present fabric is produced by way of a spunbond process. In a spunbond process, the fabrication of non-woven fabric includes the following steps: (a) extruding strands of the odor control composition from a spinneret; (b) quenching the strands with a flow of air which is generally cooled in order to hasten the solidification of the molten strands; (c) attenuating the filaments by advancing the filaments through the quench zone with a draw tension that can be applied by either pneumatically entraining the filaments in an air stream or by winding the filaments around mechanical draw rolls of the type commonly used in the textile fibers industry; (d) collecting the drawn strands into a web on a foraminous surface, e.g. moving screen or porous belt; and (e) bonding the web of loose strands into the non-woven fabric. Bonding can be achieved by a variety of means including, but not limited to, thermo-calendaring process, adhesive bonding process, hot air bonding process, needle punch process, hydroentangling process, and combinations thereof.

[0121] The spunbond non-woven fabric can be formed into multilayer or laminate structures. Such multilayer structures comprise at least two or more layers, wherein at least one or more layers are spunbond non-woven fabrics according to the present disclosure, and one or more other layers are selected from one or more melt blown non-woven layers, one or more wet-laid non-woven layers, one or more air-laid non-woven layers, one or more webs produced by any non-woven or melt spinning process, one or more film layers, such as cast film, blown film, one or more coating layers derived from a coating composition via, for example, extrusion coating, spray coating, gravure coating, printing, dipping, kiss rolling, or blade coating. The laminate structures can be joined via any number of bonding methods;

thermal bonding, adhesive lamination, hydroentangling, needle punching. Structures can range from S to SX, or SXX, or SXXX, or SXXXX, or SXXXXX, whereby the X can be a film, coating, or other non-woven material in any combination. Additional spunbond layers can be made from the ethylene-based polymer composition, as described herein, and optionally in combinations with one or more polymers and/or additives.

[0122] The spunbond non-woven fabric can be used in various end-use applications including, but not limited to, hygiene absorbent products such as diapers, feminine hygiene articles, adult incontinence products, wipes, bandages and wound dressings, and disposable slippers and footwear, medical application such as isolation gowns, surgical gowns, surgical drapes and covers, surgical scrub suits, caps, masks, and medical packaging.

[0123] In the case of staple or binder fibers, the present fibers composed of the odor control composition can be mixed with a variety of other fibers including synthetic fibers such as polyethylene (PE), polypropylene (PP), polyethylene terephthalate (PET), or natural fibers such as cellulose, rayon, or cotton. Such fibers can be wet laid, air laid or carded into a non-woven web. The non-woven web can then be laminated to other materials.

[0124] In an embodiment, the plurality of fibers of the non-woven fabric have a diameter from 0.2 microns to 10 microns.

[0125] In an embodiment, the present fiber can be used with a carding line to produce fabric.

[0126] By way of example, and not limitation, some embodiments of the present disclosure will now be described in detail in the following Examples.

EXAMPLES

[0127] Materials used in the examples are provided in Table 1 below.

Table 1

Material/Description	Properties	Source
Ethylene/octene (LLDPE 1)	0.9 melt flow rate (I2) (g/10min) 0.923 g/cc	The Dow Chemical Company
ZnO 800HSA Zinc Oxide micro-powder (ZnO-1)	ZnO D50 particle size 3000 nm; density = 5.61 g/cc; Porosity 0.0131 g/m ³ , surface area 4.46 m ² /g	Zinc Oxide, LLC

Material/Description	Properties	Source
Zinc Oxide micro-powder (ZnO-2)	ZnO D50 particle size 500 nm; density = 5.61 g/cc; Porosity 0.008 m ³ /g, surface area 3.36 m ² /g	500 nm (US Research Nanomaterials)
Zoco102 Zinc Oxide micro-powder (ZnO-3)	ZnO D50 particle size 200nm; density = 5.61 g/cc; Porosity 0.012 m ³ /g, surface area 4.4 m ² /g	Zochem, Inc.
Ampacet 110069 White PE MB Titanium dioxide (TiO ₂) Masterbatch	70 wt% TiO ₂ in Carrier Resin LLDPE (MI 2.3, d- 0.917 g/cc) Masterbatch Specific gravity: 2.03	Ampacet Corporation
Surlyn® 9150 (Zinc Ionomer)	Ethylene/Methacrylic Acid Copolymer, zinc cation Density 0.970 g/cc, melt flow 4.5 g/10min	Dow-DuPont
Cu ₂ O	325 mesh	Reade Advanced Materials

[0128] 1. Films

[0129] Master batch processing. Two master batches were prepared to ease feeding the odor suppressing compositions into a subsequent film line. The master batches were prepared on a Coperion ZSK 26 twin screw extruder using a general purpose screw. The residence time of material was controlled by the screw design, feed rate of 20 lbs/hr, and a screw speed of 300 revolutions per minute (RPM). No oil was injected. There was no side arm feeder. No vacuum was pulled. The compounded material was sent through a water bath before being cut by a strand cut pelletizer. After collection the pelletized materials were N₂ purged, then sealed in an aluminum bag.

[0130] The composition of the first master batch (MB1) was 50 wt % LLDPE 1, 25 wt% ZnO, and 25 wt% Surlyn 9150. The composition of the second master batch (MB2) was 90 wt% LLDPE 1 and 10 wt % Cu₂O. Examples and counter example formulations were generated using the appropriate amount of pure LLDPE 1, MB1 and MB2 to achieve the target weight % of each composition listed.

Table 2. Blown film line process parameters

Parameter	Units	Films without TiO ₂ MB	Films containing TiO ₂ MB
Takeoff	m/min	15	15
Layflat	cm	23.5	23.5
Frostline	cm	14	14
B.U.R	ratio	2.5	2.5
Die gap	mm	2.0	2.0
Melt temperature - Ext. A	°C	218	218
Melt temperature - Ext. B	°C	226	226
Melt temperature - Ext. C	°C	215	215
RPM - Ext. A	rpm	51	51
RPM - Ext. B	rpm	50	50
RPM - Ext. C	rpm	32	32
Total Output	kg/hr	8.8	8.8
Film Total Thickness	mm	0.023	0.056

[0131] 2. Odor Suppression

[0132] The compositions of comparative samples (CS) and inventive examples (IE) are shown in Table 3.

[0133] The odor suppression values (OSV) for are provided in Table 3 below.

Concentrations were measured using the reference sample (CS 1) as the calibration standard after two days, concentrations in the reference sample might change after two days, so the concentrations in the samples should be considered as the relative change to the reference sample.

Table 3. Odor Suppression Values and Blown Film Properties

OSV of Methyl Mercaptan		
Sample	Components	Methyl Mercaptan OSV (%)
CS 1	99% LLDPE 1 + 1% TiO ₂ MB	12
CS 2	97.5% LLDPE 1 + 2.5% TiO ₂ MB	2
CS 3	99% LLDPE 1 + 0.5 wt% ZnO + 0.5 wt% Zinc Ionomer	28
CS 4	97.5% LLDPE 1 + 1.25 wt% ZnO + 1.25 wt% Zinc Ionomer	44
IE 1	97.4% LLDPE 1 + 1.25 wt% ZnO + 1.25 wt% Zinc Ionomer + 0.1% Cu ₂ O	80
IE 2	98.9% LLDPE 1 + 0.5 wt% ZnO + 0.5 wt% Zinc Ionomer + 0.1% Cu ₂ O	64
IE 3	99.4% LLDPE 1 + 0.25 wt% ZnO + 0.25 wt% Zinc Ionomer + 0.1% Cu ₂ O	49

Zinc ionomer used in Table 3 is Surlyn 9150

*TiO₂ MB—titanium dioxide masterbatch 70 wt% TiO₂ powder in 30 wt% LLDPE carrier, added for white color

[0134] In Table 3, component amounts for each sample yield 100 wt% total sample composition. It can readily be observed that the ZnO/zinc ionomer combination is effective in improving OSV as compared to a composition that lacks any odor suppressing technology by comparing the OSV for CS 3 (28%) to the OSVs for CS 1 & 2 (12% and 2% respectively). However, it is surprising to see that although Cu₂O is added at very low loadings as part of the present odor suppressant (*i.e.*, at < 10% of the combination of ZnO, zinc ionomer, and Cu₂O in IE2), it can further improve the OSV to 64% as compared to CS 3 OSV of 28%, (*i.e.*, the sample with zinc ionomer and ZnO, and without Cu₂O present). The addition of Cu₂O unexpectedly allows for a reduction in ZnO/zinc ionomer concentrations by 50% in the composition while maintaining an OSV that is almost 50% higher than the ZnO/zinc ionomer combination that does not have Cu₂O present, as can be observed by comparing the OSV for IE3 (49%) to the OSV of CS3 (28%). It is further observed that the ZnO/zinc ionomer combination still exhibits a significant influence on OSV in that higher loadings of these materials in combination with 0.1 wt% Cu₂O exhibits the highest OSV of the inventive examples IE1 (80%) and IE2 (64%) shown in Table 3.

[0135] It is specifically intended that the present disclosure not be limited to the embodiments and illustrations contained herein, but include modified forms of those embodiments including portions of the embodiments and combinations of elements of different embodiments as come within the scope of the following claims.

CLAIMS

1. A fiber comprising:
an odor control composition, the composition comprising:
(A) from 85 wt% to 99.5 wt% of an olefin-based polymer
(B) from 15 wt% to 0.5 wt% of an odor suppressant comprising a blend of:
(i) an ionomer;
(ii) particles of zinc oxide; and
(iii) particles of copper oxide.
2. The fiber of claim 1 wherein the odor control composition has a methyl mercaptan odor suppression value of greater than 45% as measured in accordance with ASTM D5504-12.
3. The fiber of claim 1, wherein the olefin-based polymer is an ethylene/alpha-olefin copolymer.
4. The fiber of claim 1 wherein the ionomer is a zinc salt of a polymer selected from the group of ethylene/methyl-methacrylic acid, ethylene/vinyl acrylic acid, ethylene/methacrylate, ethylene/n-butyl acrylic acid, and ethylene acrylic acid.
5. The fiber of claim 1, wherein the ionomer is a zinc ionomer.
6. The fiber of claim 1, wherein the particles of zinc oxide have a D50 particle size from 100 nm to 3000 nm.
7. The fiber of claim 1, wherein the particles of zinc oxide have
a surface area from 1 m²/g to 9 m²/g; and
a porosity less than 0.020 m³/g.
8. The fiber of claim 1, wherein the particles of copper oxide are selected from the group of copper (I) oxide and copper (II) oxide.
9. The composition of claim 1, wherein the weight percent ratio between the ionomer (Bi) the zinc oxide (Bii) and the copper oxide (Biii) is from 150:100:1 to 2.9:2.5:1.
10. The fiber of claim 1 wherein the fiber is a mono-component fiber.

11. The fiber of claim 1 wherein the fiber is a bi-component fiber comprising:
 - a first component that is the odor control composition;
 - a second component that is a polymeric material different than the odor control component.
12. The fiber of claim 11 wherein the bi-component fiber has a sheath-core structure.
13. The fiber of claim 11 wherein the first component is present in the sheath.
14. A fabric comprising:
 - a plurality of fibers, the fibers comprising
 - (A) from 85 wt% to 99.5 wt% of an olefin-based polymer
 - (B) from 15 wt% to 0.5 wt% of an odor suppressant comprising a blend of:
 - (i) an ionomer;
 - (ii) particles of zinc oxide; and
 - (iii) particles of copper oxide.
15. The fabric of claim 14 wherein the odor control composition has a methyl mercaptan odor suppression value of greater than 45% as measured in accordance with ASTM D5504-12.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2019/048091

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08L23/08 D01F8/06 C08K3/22
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
D01F C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 2 221 399 A1 (NOVEKO TRADING 2008 LLC [HU]) 25 August 2010 (2010-08-25) paragraphs [0001], [0015] claim 10	1-15
Y	WO 2006/011926 A1 (CRYOVAC INC [US]; SPEER DREW V [US] ET AL.) 2 February 2006 (2006-02-02) page 8, lines 22,27,29 page 9, line 1 page 30, lines 12-14 page 30; table 8	1-15
Y	WO 2017/093541 A1 (CRYOVAC INC [US]; SPIGAROLI ROMANO [IT]; STAFYLA EIRINI [IT]) 8 June 2017 (2017-06-08) page 15, lines 10-11,30-31 tables 2,6-8	1-15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

11 November 2019

Date of mailing of the international search report

20/11/2019

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Behm, Sonja

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2019/048091

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 2221399	A1	25-08-2010	
		AU 2007361262 A1	14-05-2009
		BR PI0722265 A2	22-04-2014
		CA 2705217 A1	14-05-2009
		CN 101855393 A	06-10-2010
		EA 201000586 A1	29-10-2010
		EP 2221399 A1	25-08-2010
		IL 205229 A	28-02-2013
		JP 5520826 B2	11-06-2014
		JP 2011500972 A	06-01-2011
		KR 20100112549 A	19-10-2010
		MA 31897 B1	01-12-2010
		NZ 585145 A	28-10-2011
		TN 2010000164 A1	11-11-2011
		US 2010221969 A1	02-09-2010
		WO 2009059457 A1	14-05-2009

WO 2006011926	A1	02-02-2006	
		AT 466494 T	15-05-2010
		AU 2005267550 A1	02-02-2006
		CA 2571173 A1	02-02-2006
		EP 1773140 A1	18-04-2007
		NZ 552053 A	26-03-2010
		US 2005287318 A1	29-12-2005
		US 2007210281 A1	13-09-2007
		US 2010300905 A1	02-12-2010
		US 2013164467 A1	27-06-2013
		WO 2006011926 A1	02-02-2006

WO 2017093541	A1	08-06-2017	
		AU 2016363608 A1	17-05-2018
		BR 112018009707 A2	06-11-2018
		CN 108367551 A	03-08-2018
		EP 3383651 A1	10-10-2018
		US 2018362232 A1	20-12-2018
		WO 2017093541 A1	08-06-2017
