



(51) International Patent Classification:

D04H 1/492 (2012.01) D04H 1/732 (2012.01)

(21) International Application Number:

PCT/IB2021/000002

(22) International Filing Date:

06 January 2021 (06.01.2021)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

16/750,433 23 January 2020 (23.01.2020) US

(71) Applicant: JACOB HOLM & SONS AG [CH/CH]; Picassoplatz 8, 4052 Basel (CH).

(72) Inventors: COLLINS, Geoff; C/o Jacob Holm & Sons AG, Picassoplatz 8, 4052 Basel (CH). CHAVAN, Santosh; C/o Jacob Holm & Sons AG, Picassoplatz 8, 4052 Basel (CH).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN,

KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: NONWOVEN WEB AND METHODS TO PREPARE THE WEB




FIG. 1

(57) **Abstract:** A nonwoven web, containing at least one first homogeneous layer consisting of a blend of at least one of defibrated natural plant based fibers, individualized natural plant based fibers and staple fibers is provided. The nonwoven web contains no binder, adhesive or thermal bonding fibers and a basis weight of the at least one homogeneous layer is from 20 g/m² to 100 g/m². When a weighted average fiber length of the at least one of defibrated natural plant based fibers, individualized natural plant based fibers and staple fibers is greater than about 4.0 mm, the nonwoven web is a non-dispersible product which does not meet the requirement for dispersibility in accordance with IND A/ED ANA GD4, and when a weighted average fiber length of the at least one of defibrated natural plant based fibers, individualized natural plant based fibers and staple fibers is less than about 4.0 mm, the nonwoven web is a dispersible product as defined in accordance with IND A/ED ANA GD4. Methods to prepare the nonwoven web are provided.

